

Test report

23W-015788(A1)



PASS with information Overall result

Please refer to the following pages for test result summary and notes.

Client information

Client: SPECTOR & CO.

Address: 5700 rue Kieran, Montréal, Quebec H4S

2B5 Canada



Sample information

Description: NOMAD MUST HAVES BACKPACK

Assortment: BLK/NVY/KHA

Item no./name: BGR105 Item class: ASHBURY BAG

Country of origin: China

Country of distribution: Canada, United States

Quantity submitted: 4 pcs per color

Purchase order #: PO 72910 Factory/supplier: UST090

Labeled age grade: -Tested age grade: -

General information

Sample receipt date: 08-Nov-2023

08-Nov-2023 to 17-Nov-2023, Testing period:

28-Nov-2023 to 30-Nov-2023

Report date: 30-Nov-2023

QIMA (Hangzhou) Testing Co., Ltd.

QIMA (Hangzhou) Testing Co., Ltd.

Eric Liu

Lab Operation Director

Jeremy Xu

Chemical Laboratory Supervisor





Result summary

At the request of the client, the following test were conducted:

Test(s) conducted	Conclusion
California Proposition 65, Total Lead in Paints and Surface Coatings	PASS
California Proposition 65, Total Lead in Substrate Materials	PASS
Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead in Stickers, Films and Surface Coating Materials	PASS
Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content	PASS
California Proposition 65, Total Cadmium in Paints and Surface Coatings	PASS
California Proposition 65, Total Cadmium in Substrate Materials	PASS
Canadian Surface Coating Materials Regulations SOR/2016-193, Total Mercury in Paints and Surface Coatings	PASS
Client's requirement, Total Nickel content	Information only
Client's Requirement, Total Tungsten content	Information only
US States Requirement, Per-and Polyfluoroalkyl Substances (PFAS) Content (Total Fluorine Method)	PASS
CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)	PASS
California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)	PASS
Client's Requirement, Phthalates content	PASS
Color Fastness to Water	PASS
Color Fastness to Crocking	PASS
Color Fastness to Light	PASS
Dimensions	Information only
Article Weight	Information only
Defects	PASS
Fabric Weight Per Unit Area	Information only
Tensile Strength	PASS
Tearing Strength	PASS
Seam Strength	PASS
Abrasion Resistance	PASS
Pilling Resistance	PASS
Zipper Strength	PASS
Zipper Operability	PASS
SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile	PASS
Fiber Content	PASS
COU Test	





Test(s) conducted	Conclusion
19 CFR 134.11, Country of Origin	PASS
Marking of Imported Goods Order, (C.R.C., c.535), Country of Origin	PASS
Charter of French Language, (R.S.Q., c.C-11), Province of Quebec Labeling	PASS
Client's Requirement for Static Load Test	PASS





California Proposition 65, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4					Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	38					90
Conclusion	PASS					

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15mg/kg)

Remark:

The specification is quoted from client's requirement.





California Proposition 65, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5	6+7	8	9+10	12	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit =15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Specimen No.	Transferre	Date of Issue	
	Report No.	No. Specimen No.	
12	23W-015094(A1)	12	30-Nov-2023





Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead in Stickers, Films and Surface Coating Materials

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4					Total
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Limit (mg/kg)
Total Lead (Pb)	38					90
Conclusion	PASS					

Note:

mg/kg=Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit =15 mg/kg)





Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4	5	6+7	8	9+10	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	38	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	11	12				Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND				90
Conclusion	PASS	PASS				

Note:

mg/kg=Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Specimen No.	Transferre	Data of Issue	
	Report No.	Specimen No.	Date of Issue
12	23W-015094(A1)	12	30-Nov-2023





California Proposition 65, Total Cadmium in Paints and Surface Coatings

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4					Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND					75
Conclusion	PASS					

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Remark:

The specification is quoted from client's requirement.





California Proposition 65, Total Cadmium in Substrate Materials

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5	6+7	8	9+10	12	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND	ND	ND	ND	ND	75
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Specimen No.	Trai	Transferred from			
	Report No.	Specimen No.	Date of Issue		
12	23W-015094(A1)	12	30-Nov-2023		





Canadian Surface Coating Materials Regulations SOR/2016-193, Total Mercury in Paints and Surface Coatings

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4					Total
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Limit (mg/kg)
Total Mercury (Hg)	ND					10
Conclusion	PASS					

Note:

mg/kg=Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 10 mg/kg)





Client's requirement, Total Nickel content

Test Method: US EPA 3052:1996 & US EPA 6010D:2014

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5					Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Nickel (Ni)	ND					NA
Conclusion	Information only					

Note:

mg/kg = Milligrams per kilogram

ND = Not detected (report limit = 30 mg/kg)

NA=Not applicable





Client's Requirement, Total Tungsten content

Test Method: US EPA 3052:1996 & US EPA 6010D:2014

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5					Limit
Test Item	Result	Result	Result	Result	Result	(mg/kg)
	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	
Total Tungsten (W)	ND					NA
Conclusion	Information only					

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

NA=Not applicable





US States Requirement, Per-and Polyfluoroalkyl Substances (PFAS) Content (Total Fluorine Method)

Test Method: With reference to EN 14582:2016

Analytical Method: Ion Chromatograph

Specimen No.	1	2	3		Limit
Test Item	Result	Result	Result	Result	(mg/kg)
	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	
Per- and polyfluoroalkyl substances (PFAS) (as total fluorine)	ND	90	66		100
Conclusion	PASS	PASS	PASS		

Note:

mg/kg (Milligrams per kilogram) = ppm (Parts per million)

LT = Less than

ND = Not Detected (Reporting Limit = 50 mg/kg)

Remarks:

The limit is referenced from California AB 652 (2021-2022) and California AB 1200 (2021-2022)

Specimen No.	Transferre	ed from	Date of Issue
	Report No.	Specimen No.	Date of issue
1	23W-015094(A1)	16	30-Nov-2023
2	23W-015094(A1)	1	30-Nov-2023
3	23W-015094(A1)	2	30-Nov-2023





CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen N	0.	4	6+7	8	9+10	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusion	1	PASS	PASS	PASS	PASS	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.





CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen N	0.	12				Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND				1000
Benzyl butyl phthalate (BBP)	85-68-7	ND				1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND				1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND				1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND				1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND				1000
Diisobutyl phthalate (DIBP)	84-69-5	ND				1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND				1000
Conclusion	1	PASS				

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Specimen No	Transferre	ed from	Data of Issue
Specimen No.	Report No.	Specimen No.	Date of Issue
12	23W-015094(A1)	12	30-Nov-2023





California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		4	6+7	8	9+10	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion	1	PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.





California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		12				Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND				1000
Benzyl butyl phthalate (BBP)	85-68-7	ND				1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND				1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND				1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND				1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND				1000
Conclusion	1	PASS				

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Specimen No	Transferre	ed from	Date of Issue
Specimen No.	Report No.	Specimen No.	Date of Issue
12	23W-015094(A1)	12	30-Nov-2023





Client's Requirement, Phthalates content

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No	o.	4	6+7	8	9+10	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	ND	ND	ND	1000
Diethyl phthalate (DEP)	84-66-2	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND	ND	ND	ND	1000
Conclusion	1	PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.





Client's Requirement, Phthalates content

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No	o.	12				Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND				1000
Benzyl butyl phthalate (BBP)	85-68-7	ND				1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND				1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND				1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND				1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND				1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND				1000
Diethyl phthalate (DEP)	84-66-2	ND				1000
Diisobutyl phthalate (DIBP)	84-69-5	ND				1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND				1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND				1000
Conclusion	1	PASS				

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Specimen No.	Transferre	Data of Issue	
	Report No.	Specimen No.	Date of Issue
12	23W-015094(A1)	12	30-Nov-2023





Color Fastness to Water

Test Method: AATCC 107-2022.

Specimen No.	13	14	15			Client's
Items	Result (Grade)	Result (Grade)	Result (Grade)	Result (Grade)	Result (Grade)	requirement
Change in shade	4.5	4.5	4.5			-
Staining on multi- fiber stripe						
-Acetate	4.0	4.0	4.0			Min. 3.5
-Cotton	4.5	4.5	4.5			Min. 3.5
-Nylon	4.0	4.0	4.0			Min. 3.5
-Polyester	4.5	4.5	4.5			Min. 3.5
-Acrylic	4.5	4.5	4.5			Min. 3.5
-Wool	4.5	4.5	4.5			Min. 3.5
Conclusion	PASS	PASS	PASS			-

Remark: Grey scale rating is based on the 5-step of 1 to 5, where 1 is bad and 5 is good.


Color Fastness to Crocking

Test Method: AATCC 8-2016

Specimen No.	13	14	15			Client's
Items	Result (Grade)	Result (Grade)	Result (Grade)	Result (Grade)	Result (Grade)	requirement
Dry staining	4.0	4.0	4.0			Min. 4.0
Wet staining	4.0	4.0	4.0			Min. 2.5
Conclusion	PASS	PASS	PASS			-

Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.





Color Fastness to Light

Test Method: AATCC 16.3-2020; Option 3; Xenon Arc Lamp.

Specimen No.	13	14	15			Client's
Items	Result (Grade)	Result (Grade)	Result (Grade)	Result (Grade)	Result (Grade)	requirement
After 20 AFU Change in shade	4.5	4.5	4.0			Min. 4.0
Conclusion	PASS	PASS	PASS			-

Remarks: Grey scale rating is based on the 5-step of 1 to 5, where 1 is bad and 5 is good.

Dimensions

Test Method: IHTM, Standard Measure

Specimen No.	13	14	15			
Items	Result (cm)	Result (cm)	Result (cm)	Result (cm)	Result (cm)	Requirement
Length	28.0	28.0	28.0			N/A
Width	17.0	17.0	17.0			N/A
Height	45.0	45.0	45.0			N/A
Conclusion	Information only	Information only	Information only			





Article Weight

Test Method: With reference to IHTM-TXHZ-010

Specimen No.	13				
Items	Client's requirement	Result	Conclusion		
Article Weight (g/piece)	N/A	574	Information only		

Specimen No.	14				
Items	Client's requirement	Result	Conclusion		
Article Weight (g/piece)	N/A	573	Information only		

Specimen No.	15				
Items	Client's requirement	Result	Conclusion		
Article Weight (g/piece)	N/A	570	Information only		



Defects

Test Method: ASTM D3990 – 12(2020); Visual Examination

Conclusion

, ,			
Specimen No.	13	Dogwinowood	
Item	Result	Requirement	
Observation	No major defect	Satisfactory	
Conclusion	PASS	-	
Specimen No.	14	Doguiromont	
Item	Result	Requirement	
Observation	No major defect	Satisfactory	

Specimen No.	15	Requirement	
Item	Result		
Observation	No major defect	Satisfactory	
Conclusion	PASS	-	

PASS





Fabric Weight Per Unit Area

Test Method: ASTM D3776/D3776M-20, Option C

Specimen No.	16	17	18	19	20	Client's
Items	Result	Result	Result	Result	Result	requirement
(g/m²)	271	69.6	276	262	276	N/A
(oz/yd²)	7.99	2.05	8.14	7.73	8.14	N/A
Conclusion	Information only	-				

Specimen No.	21	22	23	24		Client's
Items	Result	Result	Result	Result	Result	requirement
(g/m²)	69.6	260	276	69.6		N/A
(oz/yd²)	2.05	7.67	8.14	2.05		N/A
Conclusion	Information only	Information only	Information only	Information only		-

Specimen No.	Transferr	Data of Issue	
	Report No.	Specimen No.	Date of Issue
16	23W-015094(A1)	20	30-Nov-2023
18	23W-015094(A1)	22	30-Nov-2023
19	23W-015094(A1)	23	30-Nov-2023
20	23W-015094(A1)	24	30-Nov-2023
22	23W-015094(A1)	26	30-Nov-2023
23	23W-015094(A1)	27	30-Nov-2023





Tensile Strength

Test Method: ASTM D5034-21

Specimen No.	16	Client's
Items	Result (lbf)	requirement (lbs)
Warp	318.7	Min. 25
Weft	278.6	Min. 25
Conclusion	PASS	-

Remark: All the warp and weft specimens were jaw broken.

Tensile Strength

Test Method: ASTM D5034-21

Specimen No.	17	Client's
Items	Result (lbf)	requirement (Ibs)
Warp	140.1	Min. 25
Weft	89.9	Min. 25
Conclusion	PASS	-

Specimen No.	Tra	Transferred from		
	Report No.	Specimen No.	Date of Issue	
16	23W-015094(A1)	20	30-Nov-2023	





Tensile Strength

Test Method: ASTM D5034-21

Specimen No.	18	Client's
Items	Result (lbf)	requirement (lbs)
Warp	379.1	Min. 25
Weft	314.5	Min. 25
Conclusion	PASS	-

Remark: All the warp and weft specimens were jaw broken.

Tensile Strength

Test Method: ASTM D5034-21

Specimen No.	19	Client's
Items	Result (lbf)	requirement (lbs)
Warp	333.3	Min. 25
Weft	278.1	Min. 25
Conclusion	PASS	-

Remark: All the warp specimens were jaw broken.

Specimen No.	Trar	Transferred from		
	Report No.	Specimen No.	Date of Issue	
18	23W-015094(A1)	22	30-Nov-2023	
19	23W-015094(A1)	23	30-Nov-2023	





Tensile Strength

Test Method: ASTM D5034-21

Specimen No.	20	Client's
Items	Result (lbf)	requirement (lbs)
Warp	379.1	Min. 25
Weft	314.5	Min. 25
Conclusion	PASS	-

Remark: All the warp and weft specimens were jaw broken.

Tensile Strength

Test Method: ASTM D5034-21

Specimen No.	21	Client's
Items	Result (lbf)	requirement (lbs)
Warp	140.1	Min. 25
Weft	89.9	Min. 25
Conclusion	PASS	-

Specimen No.	Transferre	Data of laws	
	Report No.	Specimen No.	Date of Issue
20	23W-015094(A1)	24	30-Nov-2023





Tensile Strength

Test Method: ASTM D5034-21

Specimen No.	22	Client's
Items	Result (lbf)	requirement (lbs)
Warp	322.9	Min. 25
Weft	262.4	Min. 25
Conclusion	PASS	-

Remark: All the warp specimens were jaw broken.

Tensile Strength

Test Method: ASTM D5034-21

Specimen No.	23	Client's
Items	Result (lbf)	requirement (lbs)
Warp	379.1	Min. 25
Weft	314.5	Min. 25
Conclusion	PASS	-

Remark: All the warp and weft specimens were jaw broken.

Considerate No.	Trai	nsferred from	Data of Issue
Specimen No.	Report No.	Specimen No.	Date of Issue
22	23W-015094(A1)	26	30-Nov-2023
23	23W-015094(A1)	27	30-Nov-2023





Tensile Strength

Test Method: ASTM D5034-21

Specimen No.	24	Client's requirement
Items	Result (lbf)	(lbs)
Warp	140.1	Min. 25
Weft	89.9	Min. 25
Conclusion	PASS	-





Tearing Strength

Test Method: ASTM D1424-21; Elmendorf

Specimen No.	16	17	18	19	20	Client's
Items	Result	Result	Result	Result	Result	requirement
Warp yarns torn (lbf)	7.7	6.7	>14.1	10.8	>14.1	Min. 1.5
Weft yarns torn (lbf)	9.0	5.6	>14.1	11.8	>14.1	Min. 1.5
Conclusion	PASS	PASS	PASS	PASS	PASS	-

Specimen No.	21	22	23	24		Client's
Items	Result	Result	Result	Result	Result	requirement
Warp yarns torn (lbf)	6.7	10.8	>14.1	6.7		Min. 1.5
Weft yarns torn (lbf)	5.6	11.0	>14.1	5.6		Min. 1.5
Conclusion	PASS	PASS	PASS	PASS		-

Note:

- (1) Warp test test in which the warp yarns are torn. Weft test test in which the weft yarns are torn.
- (2) The maximum capacity of the tester is 14.1lbf.

Specimen No.	Transferre	ed from	Date of Issue
specimen No.	Report No.	Specimen No.	Date of issue
16	23W-015094(A1)	20	30-Nov-2023
18	23W-015094(A1)	22	30-Nov-2023
19	23W-015094(A1)	23	30-Nov-2023
20	23W-015094(A1)	24	30-Nov-2023
22	23W-015094(A1)	26	30-Nov-2023
23	23W-015094(A1)	27	30-Nov-2023





Seam Strength

Test Method: With reference to ASTM D 1683/D1683M-22

Specimen No.	13			
Items	Client's requirement	Result	Conclusion	
Side seam (lbf)	Min. 25	78.2(S.T.B.)	DACC	
Bottom seam (lbf)	Min. 25	158.6(S.T.B.)	PASS	

Specimen No.	14			
Items	Client's requirement	Result	Conclusion	
Side seam (lbf)	Min. 25	73.7(S.T.B.)	PASS	
Bottom seam (lbf)	Min. 25	192.2(S.T.B.)	PASS	

Specimen No.	15			
Items	Client's requirement	Result	Conclusion	
Side seam (lbf)	Min. 25	65.4(S.T.B.)	DACC	
Bottom seam (lbf)	Min. 25	140.6(S.T.B.)	PASS	

Remarks: S.T.B. = Sewing Thread Break





Abrasion Resistance

Test Method: ASTM D4966-12(2016), Option 1; Martindale Wear & Abrasion Tester; 12kPa Pressure

Specimen No.	16	18	19	20	22	Client's
Items	Result	Result	Result	Result	Result	requirement
End point (rubs)	>7500	>7500	>7500	>7500	>7500	7500
Conclusion	PASS	PASS	PASS	PASS	PASS	-

Specimen No.	23					Client's
Items	Result	Result	Result	Result	Result	requirement
End point (rubs)	>7500					7500
Conclusion	PASS					-

Specimen No.	Transferre	ed from	Date of Issue
	Report No.	Specimen No.	Date of issue
16	23W-015094(A1)	20	30-Nov-2023
18	23W-015094(A1)	22	30-Nov-2023
19	23W-015094(A1)	23	30-Nov-2023
20	23W-015094(A1)	24	30-Nov-2023
22	23W-015094(A1)	26	30-Nov-2023
23	23W-015094(A1)	27	30-Nov-2023





Pilling Resistance

Test Method: ASTM D3512/D3512M-22; After 30 min. tumbling in Random tumble Pilling Tester

Specimen No.	16	18	19	20	22	Client's
Items	Result	Result	Result	Result	Result	requirement
As received Rating	4.0	4.0	4.0	4.0	4.0	Min. 3.5
Conclusion	PASS	PASS	PASS	PASS	PASS	-

Specimen No.	23					Client's
Items	Result	Result	Result	Result	Result	requirement
As received Rating	4.0					Min. 3.5
Conclusion	PASS					-

Remarks: Pilling Rating

- 5 No pilling/ No fuzzing
- 4 Slight pilling/Slight fuzzing
- 3 Moderate pilling/ Moderate fuzzing
- 2 Severe pilling/ Severe fuzzing
- 1 Very severe pilling/ Very severe fuzzing

Specimen No.	Transferre	Data of leave	
	Report No.	Specimen No.	Date of Issue
16	23W-015094(A1)	20	30-Nov-2023
18	23W-015094(A1)	22	30-Nov-2023
19	23W-015094(A1)	23	30-Nov-2023
20	23W-015094(A1)	24	30-Nov-2023
22	23W-015094(A1)	26	30-Nov-2023
23	23W-015094(A1)	27	30-Nov-2023





Zipper Strength

Test Method: ASTM D2061-07(2021); type: LM

Specimen No.	25		
Items	Result	Client's requirement	
Chain Crosswise Strength Test (lbf)	197(Tape separate)	Min. 175	
Resistance to Pull-Off Slider Pull (lbf)	42(Puller pull out)	Min.35	
Resistance to Twist of Pull and Slider Test Clockwise (In. lbf) Counter-Clockwise (In. lbf)	5.4(Slider break) 6.1(Slider break)	Min.4	
Conclusion	PASS		

Specimen No.	26	
Items	Result	Client's requirement
Chain Crosswise Strength Test (lbf)	197(Tape separate)	Min. 175
Resistance to Pull-Off Slider Pull (lbf)	42(Puller pull out)	Min.35
Resistance to Twist of Pull and Slider Test Clockwise (In. lbf) Counter-Clockwise (In. lbf)	5.4(Slider break) 6.1(Slider break)	Min.4
Conclusion	PASS	

Specimen No.	27		
Items	Result	Client's requirement	
Chain Crosswise Strength Test (lbf)	197(Tape separate)	Min. 175	
Resistance to Pull-Off Slider Pull (lbf)	42(Puller pull out)	Min.35	
Resistance to Twist of Pull and Slider Test Clockwise (In. lbf) Counter-Clockwise (In. lbf)	5.4(Slider break) 6.1(Slider break)	Min.4	
Conclusion	PASS		





Zipper Operability

Test Method: ASTM D2062-03(2021)

Specimen No.	25		
Items	Result	Client's requirement	
Chain opening (lbf)	0.3	Max. 2	
Chain closing (lbf)	0.4	Max. 2	
Conclusion	PASS		

Specimen No.	26		
Items	Result	Client's requirement	
Chain opening (lbf)	0.3	Max. 2	
Chain closing (lbf)	0.4	Max. 2	
Conclusion	PASS		

Specimen No.	27		
Items	Result	Client's requirement	
Chain opening (lbf)	0.3	Max. 2	
Chain closing (lbf)	0.4	Max. 2	
Conclusion	PASS		



SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2023

Specimen No.	13-Shell				
Preliminary Tests	<u>Fabric Surface</u>	Smooth	Test Specimen Direction		Face Length
	Result				
Items	As Received		After Dry-cleaning and Laundering*		Client's requirement
	Flame Spread (sec.)	Burn Code	Flame Spread (sec.)	Burn Code	
(1)	-	DNI	-	DNI	
(2)	-	DNI	-	DNI	
(3)	-	DNI	-	DNI	>3.5s
(4)	-	DNI	-	DNI	
(5)	-	DNI	-	DNI	
Conclusion	PASS				

^{*} Dry-cleaning / Laundering procedure is according to Commercial Dry Cleaning / CAN/CGSB-4.2 No.58-2019, Procedure 5, Dry Procedure D1; Moderate mechanical action at 50° C, Synthetic detergent, Tumble dry normal.

Burn Code Description:

DNI = Did not ignite;





SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2023

Specimen No.			13-Lining		
Preliminary Tests	Fabric Surface	Smooth	Test Specime	n Direction	Face Length
		Re	esult		
Items	As Reco	eived	After Dry-cle Launde		Client's requirement
	Flame Spread (sec.)	Burn Code	Flame Spread (sec.)	Burn Code	·
(1)	-	IBE	-	IBE	
(2)	-	IBE	-	IBE	
(3)	-	IBE	-	IBE	
(4)	-	IBE	-	IBE	
(5)	-	IBE	-	IBE	.2.50
(6)	-	IBE	-	IBE	>3.5s
(7)	-	IBE	-	IBE	
(8)	-	IBE	-	IBE	
(9)	-	IBE	-	IBE	
(10)	-	IBE	-	IBE	
Conclusion			PASS		

^{*} Dry-cleaning / Laundering procedure is according to Commercial Dry Cleaning / CAN/CGSB-4.2 No.58-2019, Procedure 5, Dry Procedure D1; Moderate mechanical action at 50° C, Synthetic detergent, Tumble dry normal.

Burn Code Description:

IBE = Ignited but extinguished;





SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2023

Specimen No.	14-Shell				
Preliminary Tests	Fabric Surface	Smooth	Test Specime	n Direction	Face Length
		Re	esult		
Items	As Reco	eived	After Dry-cle Launde		Client's requirement
	Flame Spread (sec.)	Burn Code	Flame Spread (sec.)	Burn Code	'
(1)	-	DNI	-	DNI	
(2)	-	DNI	-	DNI	
(3)	-	DNI	-	DNI	>3.5s
(4)	-	DNI	-	DNI	
(5)	-	DNI	-	DNI	
Conclusion			PASS		

^{*} Dry-cleaning / Laundering procedure is according to Commercial Dry Cleaning / CAN/CGSB-4.2 No.58-2019, Procedure 5, Dry Procedure D1; Moderate mechanical action at 50° C, Synthetic detergent, Tumble dry normal.

Burn Code Description:

DNI = Did not ignite;





SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2023

Specimen No.			14-Lining		
Preliminary Tests	Fabric Surface	Smooth	Test Specime	n Direction	Face Length
		Re	esult		
Items	As Reco	eived	After Dry-cle Launde		Client's requirement
	Flame Spread (sec.)	Burn Code	Flame Spread (sec.)	Burn Code	'
(1)	-	IBE	-	IBE	
(2)	-	IBE	-	IBE	
(3)	-	IBE	-	IBE	
(4)	-	IBE	-	IBE	
(5)	-	IBE	-	IBE	. 2.5-
(6)	-	IBE	-	IBE	>3.5s
(7)	-	IBE	-	IBE	
(8)	-	IBE	-	IBE	
(9)	-	IBE	-	IBE	
(10)	-	IBE	-	IBE	
Conclusion			PASS		

^{*} Dry-cleaning / Laundering procedure is according to Commercial Dry Cleaning / CAN/CGSB-4.2 No.58-2019, Procedure 5, Dry Procedure D1; Moderate mechanical action at 50° C, Synthetic detergent, Tumble dry normal.

Burn Code Description:

IBE = Ignited but extinguished;





SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2023

Specimen No.	15-Shell				
Preliminary Tests	<u>Fabric Surface</u>	Smooth	Test Specime	n Direction	Face Length
		Re	esult		
Items	As Reco	eived	After Dry-cle Launde		Client's requirement
	Flame Spread (sec.)	Burn Code	Flame Spread (sec.)	Burn Code	'
(1)	-	DNI	-	DNI	
(2)	-	DNI	-	DNI	
(3)	-	DNI	-	DNI	>3.5s
(4)	-	DNI	-	DNI	
(5)	-	DNI	-	DNI	
Conclusion			PASS		

^{*} Dry-cleaning / Laundering procedure is according to Commercial Dry Cleaning / CAN/CGSB-4.2 No.58-2019, Procedure 5, Dry Procedure D1; Moderate mechanical action at 50° C, Synthetic detergent, Tumble dry normal.

Burn Code Description:

DNI = Did not ignite;





SOR/2016-194-Textile Flammability Regulations-Non-bedding Textile

Test Method: CAN/CGSB-4.2 No.27.5-2023

Specimen No.			15-Lining		
Preliminary Tests	Fabric Surface	Smooth	Test Specime	n Direction	Face Length
	Result				
Items	As Reco	eived	After Dry-cle Launde		Client's requirement
	Flame Spread (sec.)	Burn Code	Flame Spread (sec.)	Burn Code	'
(1)	-	IBE	-	IBE	
(2)	-	IBE	-	IBE	
(3)	-	IBE	-	IBE	
(4)	-	IBE	-	IBE	
(5)	-	IBE	-	IBE	
(6)	-	IBE	-	IBE	>3.5s
(7)	-	IBE	-	IBE	
(8)	-	IBE	-	IBE	
(9)	-	IBE	-	IBE	
(10)	-	IBE	-	IBE	
Conclusion			PASS		

^{*} Dry-cleaning / Laundering procedure is according to Commercial Dry Cleaning / CAN/CGSB-4.2 No.58-2019, Procedure 5, Dry Procedure D1; Moderate mechanical action at 50° C, Synthetic detergent, Tumble dry normal.

Burn Code Description:

IBE = Ignited but extinguished;





Fiber Content

Test Method: AATCC TM20-2021

Specimen No.		13-Shell				
Items	Client's requirement	Result	Conclusion			
Polyester (%)	100	100	PASS			
Specimen No.		13-Lining				
Items	Client's requirement	Result	Conclusion			
Polyester (%)	100	100	PASS			
Specimen No.		14-Shell				
Items	Client's requirement	Result	Conclusion			
Polyester (%)	100	100	PASS			
Specimen No.		14-Lining	1			
Items	Client's requirement	Result	Conclusion			
Polyester (%)	100	100	PASS			
Specimen No.		15-Shell				
Items	Client's requirement	Result	Conclusion			
Polyester (%)	100	100	PASS			
Specimen No.		15-Lining				
Items	Client's requirement	Result	Conclusion			
Polyester (%)	100	100	PASS			



Fiber Content

Test Method: AATCC TM20-2021/AATCC TM20A-2021; based on moisture regain weight.

Specimen No.	13-Mesh				
Items	Client's requirement	Result	Conclusion		
Polyester (%)	88±3	87.7	DACC		
Spandex (%)	12±3	12.3	PASS		

Specimen No.	14-Mesh				
Items	Client's requirement	Result	Conclusion		
Polyester (%)	88±3	87.7	DACC		
Spandex (%)	12±3	12.3	PASS		

Specimen No.	15-Mesh				
Items	Client's requirement	Result	Conclusion		
Polyester (%)	88±3	87.7	DACC		
Spandex (%)	12±3	12.3	PASS		

Note: Based on ASTM D1909-13, Moisture regain of Polyester: 0.4%, Spandex: 1.3%.





19 CFR 134.11, Country of Origin

Test Parameters	Observation	Conclusion
Country of Origin	Present on product and is visible to the consumer at the point of sale.	PASS

Marking of Imported Goods Order, (C.R.C., c.535), Country of Origin

Section	Requirement	Conclusion
2	Country of Origin Markings	PASS

Charter of French Language, (R.S.Q., c.C-11), Province of Quebec Labeling

Clause	Test	Conclusion
c.C-11	French Labeling	PASS





Client's Requirement for Static Load Test

Test Item	Test Method	Requirement	Conclusion
Static Load Test	 Visual check the normal function of the sample under test as received. Hanging the bag in a proper place. Place the test load on the bag with 50lb for 2 hours. Observe and record any failure, structural breakage, deformation or any other unusual change from the original state of sample. 	No failure, No structural breakage, No damage	PASS





Specimen description

Specimen #	Specimen description	Location
1	Charcoal grey textile	Main body (charcoal grey style)
2	Dark green textile	Main body (dark green style)
3	Navy textile	Main body (navy style)
4	Black coating	Zipper head (all styles)
5	Silvery metal	Zipper puller (charcoal grey style)
6	Black soft plastic	Zipper teeth (charcoal grey style)
7	Black soft plastic	Side elastic (charcoal grey style)
8	Black plastic	Adjustable buckle (charcoal grey style)
9	Black foam	Main body filler (charcoal grey style)
10	Black foam	Filler of handle back surface (charcoal grey style)
11	Black non-woven textile	Filler of handle (charcoal grey style)
12	Black coated white label	Composition label (charcoal grey style)
13	Dark green bag	Finished product
14	Navy bag	Finished product
15	Charcoal grey bag	Finished product
16	Green shell upper fabric	Raw material(dark green style)
17	Black lining fabric	Raw material(dark green style)
18	Black shell bottom fabric	Raw material(dark green style)
19	Navy shell upper fabric	Raw material (navy style)
20	Black shell bottom fabric	Raw material (navy style)
21	Black lining fabric	Raw material (navy style)
22	Grey shell upper fabric	Raw material(charcoal grey style)
23	Black shell bottom fabric	Raw material (charcoal grey style)
24	Black lining fabric	Raw material (charcoal grey style)
25	Black zipper	Raw material(dark green style)
26	Black zipper	Raw material (navy style)
27	Black zipper	Raw material(charcoal grey style)





Pictures

Sample photo:









Pictures

Product reference photo:

4*13.3cm

ASHBURY

■Y SPECTOR & CO.

SHELL:100% POST-CONSUMER RECYCLED POLYESTER LINING:100% POLYESTER COQUILLE:100% POLYESTER

RECYCLÉ POST-CONSOMMATION DOUBLURE:100% POLYESTER

ARMAZÓN:100% POLIÉSTER RECICLADO POSTCONSUMO FORRO:100% POLIÉSTER

MESH:88% POLIESTER
12% SPANDEX
MAILLE:88% POLYESTER
12% ÉLASTHANNE
MALLA:88% POLIÉSTER
12% ELASTANE

MADE IN CHINA FABRIQUÉ EN CHINE HECHO EN CHINA

SPOT CLEAN ONLY.
NETTOYAGE CIBLE
SEULEMENT.
SOLO QUITAR
MANCHAS.



SPECTOR & CO.

C/100121

The photo was provided by the client.

End of the report

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and the method /regulation section(s) tested as described herein. If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule. (https://www.qima.com/conditions-of-service#decisionRule). This test report may not be reproduced in whole or in part, without the written approval of QIMA (Hangzhou) Testing Co., Ltd.

