



# Test Report

No.: 68.431.23.4758.02

Date: 2024-03-18

**Applicant:** Spector & Co  
**Address:** /  
**Product Name:** 12 OZ/ 350 ML DOUBLE WALL VACUUM INSULATED BOTTLE  
**Product Type / End Use:** DRINKWARE  
**Item No.:** DW304  
**Style No.:** TRENDSETTER MINI  
**Supplier:** USS049  
**Country of Origin:** CHINA  
**Country of Destination:** CANADA & U.S.A.  
**Receipt Date of Sample:** 2023-12-28, 2024-01-17, 2024-02-05, 2024-03-12  
**Date of Testing:** From 2024-01-02 to 2024-03-18  
**Sample Submitted:** The sample(s) was (were) submitted by applicant and identified.  
**Test Result:** Refer to the data listed in following pages

Test Item	Conclusion
1. US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials	Pass*
2. US California Proposition 65 - Total Cadmium Content Test - Substrate Materials	Pass*
3. US California Proposition 65 - Total lead Content Test - Paint and Similar Surface-Coating Materials	Pass*
4. US California Proposition 65 - Total Lead Content Test - Substrate Materials	Pass*
5. Phthalates Content (11P)	Pass*
6. Tungsten Content Test	Report As Is
7. Canada Consumer Product Safety Act (S.C. 2010, c. 21), Surface Coating Materials Regulations SOR/2016-193 and SOR/2022-122 - Total Mercury	Pass
8. Canada Consumer Product Safety Act (S.C. 2010, c. 21), Surface Coating Materials Regulations SOR/2016-193 and SOR/2022-122 - Total Lead	Pass
9. Canadian Consumer Products Containing Lead Regulations SOR/2018-83 - Total Lead Content Test	Pass
10. Total Nickel Content Test	Report As Is
11. U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P)	Pass
12. US California Proposition 65 - Phthalates Content (6P)	Pass*
13. Bisphenol A Content	Pass*
14. FDA CFR Title 21 Part 177.1210	Pass
15. FDA CFR Title 21 Part 177.1520	Pass
16. Total Chromium Content	Pass

Regd. Office: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch  
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998  
Fax: +86 755 8828 5299  
E-mail: info@tuv sud.com  
Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing  
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:  
Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

# Test Report

No.: 68.431.23.4758.02

Date: 2024-03-18



- Remarks:
1. MDL = Method Detection Limit
  2. N.D. = Not Detected (<MDL)
  3. ≤ Less than
  4. 1 mg/kg = 1 ppm = 0.0001%
  5. NA=Not Applicable

**TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch  
Testing Center**

Prepared by:

Authorized by:



**Huang, Jessica**  
Senior Project Coordinator

**Shu, Steven**  
Senior Project Coordinator

**Note:**

- (1) The TÜV SÜD Certification and Testing (China) Co., Ltd. "General Terms & Conditions" applied.  
Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.  
For further details, please see "Testing and certification regulation", chapter A-3.4  
For full version, please visit: EN : <https://www.tuvsud.cn/zh-cn/resource/terms-and-conditions---en> ; SCN: <https://www.tuvsud.cn/zh-cn/terms-and-conditions> ; TCN: <https://www.tuvsud.com/zh-tw/terms-and-conditions>
- (2) The results relate only to the items tested.
- (3) The test report shall not be reproduced except in full without the written approval of the laboratory
- (4) If relevant standards do not specify decision rule(s), follow decision rule as below:  
- "Pass" means that the measured result is within the limits, even when extended by expanded uncertainty at a level of confidence of 95%.  
- "Fail" means that the measured result is beyond the limit, even when extended by expanded uncertainty at a level of confidence of 95%.
- (5) The test item and sample were specified by the client.
- (6) """" denotes the conclusion was drawn according to the client's specification.

Regd. Office: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch  
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,  
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998  
Fax: +86 755 8828 5299  
E-mail: [info@tuvsud.com](mailto:info@tuvsud.com)  
Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Description of Tested Subject:

Sample	Description	Photo
A	Whole product	
001	White coating (On lid & bottle)	
002	Red coating (On lid & bottle)	

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch  
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,  
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com


Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Sample	Description	Photo
003	Steel grey coating (On lid & bottle)	
004	Black PP-CO plastic (Lid & moth)	
005	Translucent white silicone (Sealing ring)	
006	Silver stainless steel 304 (Inner body)	
007	Silver stainless steel 201 (Lid & outside body)	
008	Black silicone (Bottom pad)	

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch  
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,  
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998  
 Fax: +86 755 8828 5299  
 E-mail: info@tuvsud.com  
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

# Test Report

No.: 68.431.23.4758.02

Date: 2024-03-18



Sample	Description	Photo
010	Black coating (On lid & bottle)	
011	Rubber oil (On lid & bottle)	

T. No	Sample	Description
T1	001	White coating (On lid & bottle)
T2	002	Red coating (On lid & bottle)
T3	003	Steel grey coating (On lid & bottle)
T4	004	Black PP-CO plastic (Lid & moth)
T5	005	Translucent white silicone (Sealing ring)
T6	006	Silver stainless steel 304 (Inner body)
T7	007	Silver stainless steel 201 (Lid & outside body)
T8	008	Black silicone (Bottom pad)
T9	010	Black coating (On lid & bottle)
T10	011	Rubber oil (On lid & bottle)

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch  
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,  
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: [info@tuvsud.com](mailto:info@tuvsud.com)

Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



**Test Result(s):**

**1. US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials**

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
001+002+003	mg/kg	10	75	N.D.	Pass
010	mg/kg	10	75	N.D.	Pass
011	mg/kg	10	75	N.D.	Pass

**Remark:**

- The test results of the sample 011 is transferred from sample 015 of report 68.431.23.4283.

**2. US California Proposition 65 - Total Cadmium Content Test - Substrate Materials**

Test with reference to acid digestion or microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
004	mg/kg	10	75	N.D.	Pass
005+008	mg/kg	10	75	N.D.	Pass
006	mg/kg	10	75	N.D.	Pass
007	mg/kg	10	75	N.D.	Pass

**3. US California Proposition 65 - Total Lead Content Test - Paint and Similar Surface-Coating Materials**

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
001+002+003	mg/kg	10	90	N.D.	Pass
010	mg/kg	10	90	55.0	Pass
011	mg/kg	10	90	N.D.	Pass

**Remark:**

- The test results of the sample 011 is transferred from sample 015 of report 68.431.23.4283.

**4. US California Proposition 65 - Total Lead Content Test - Substrate Materials**

Test with reference to acid digestion or microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
004	mg/kg	10	100	N.D.	Pass
005+008	mg/kg	10	100	N.D.	Pass
006	mg/kg	10	100	N.D.	Pass
007	mg/kg	10	100	N.D.	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch  
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,  
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998  
 Fax: +86 755 8828 5299  
 E-mail: info@tuv sud.com  
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

# Test Report

No.: 68.431.23.4758.02

Date: 2024-03-18



## 5. Phthalates Content (11P)

Test with reference to in-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS).

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					001+002+003	004
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
<b>Conclusion</b>					<b>Pass</b>	<b>Pass</b>

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					005+008	010
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	0.022
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0	%	0.005	0.1	N.D.	N.D.

Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch  
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,  
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

# Test Report

No.: 68.431.23.4758.02

Date: 2024-03-18



Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
<b>Conclusion</b>					<b>Pass</b>	<b>Pass</b>

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					011	
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.	
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.	
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	
Di-isodecyl phthalate, (DIDP)	26761-40-0	%	0.005	0.1	N.D.	
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	
<b>Conclusion</b>					<b>Pass</b>	

**Remark:**

- The test results of the sample 011 is transferred from sample 015 of report 68.431.23.4283.

**6. Tungsten Content Test**

Test with reference to acid digestion and determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES)

Test items	Unit	MDL	Maximum Permissible Limit	Result(s)	
				007	
Tungsten(W)	mg/kg	10.0	-	N.D.	
<b>Conclusion</b>				<b>Report As Is</b>	

Regd. Office: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch  
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998  
 Fax: +86 755 8828 5299  
 E-mail: info@tuv sud.com  
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China  
 Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China





**7. Canada Consumer Product Safety Act (S.C. 2010, c. 21), Surface Coating Materials Regulations SOR/2016-193 and SOR/2022-122 - Total Mercury**

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
001	mg/kg	10	10.0	N.D.	Pass
002	mg/kg	10	10.0	N.D.	Pass
003	mg/kg	10	10.0	N.D.	Pass
010	mg/kg	10	10.0	N.D.	Pass
011	mg/kg	10	10.0	N.D.	Pass

Remark:

- The test results of the sample 011 is transferred from sample 015 of report 68.431.23.4283.

**8. Canada Consumer Product Safety Act (S.C. 2010, c. 21), Surface Coating Materials Regulations SOR/2016-193 and SOR/2022-122 - Total Lead**

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
001+002+003	mg/kg	10	90	N.D.	Pass
010	mg/kg	10	90	55.0	Pass
011	mg/kg	10	90	N.D.	Pass

Remark:

- The test results of the sample 011 is transferred from sample 015 of report 68.431.23.4283.

**9. Canadian Consumer Products Containing Lead Regulations SOR/2018-83 - Total Lead Content Test**

Test with reference to acid digestion or microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
001+002+003	mg/kg	10	90	N.D.	Pass
004	mg/kg	10	90	N.D.	Pass
005+008	mg/kg	10	90	N.D.	Pass
006	mg/kg	10	90	N.D.	Pass
007	mg/kg	10	90	N.D.	Pass
010	mg/kg	10	90	55.0	Pass
011	mg/kg	10	90	N.D.	Pass

Remark:

- The test results of the sample 011 is transferred from sample 015 of report 68.431.23.4283.



**10. Total Nickel Content Test**

Test with reference to acid digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
006	mg/kg	5	-	94346.247	Report As Is
007	mg/kg	5	-	18858.131	Report As Is

**11. U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P)**

Test with reference to in-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS).

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					001+002+003	004
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
<b>Conclusion</b>					<b>Pass</b>	<b>Pass</b>

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					005+008	010
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	0.022
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates	131-18-0	%	0.005	0.1	N.D.	N.D.

Regd. Office: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch  
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998  
 Fax: +86 755 8828 5299  
 E-mail: info@tuv sud.com  
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China  
 Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

# Test Report

No.: 68.431.23.4758.02

Date: 2024-03-18



(DnPP)						
<b>Conclusion</b>					<b>Pass</b>	<b>Pass</b>

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					011	
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	
<b>Conclusion</b>					<b>Pass</b>	

**Remark:**

- The test results of the sample 011 is transferred from sample 015 of report 68.431.23.4283.

**12. US California Proposition 65 - Phthalates Content (6P)**

Test with reference to in-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS).

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					001+002+003	004
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
<b>Conclusion</b>					<b>Pass</b>	<b>Pass</b>

Parameter	CAS No.	Unit	MDL	Client's	Result(s)
-----------	---------	------	-----	----------	-----------

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch  
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998  
 Fax: +86 755 8828 5299  
 E-mail: info@tuvsud.com  
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

# Test Report

No.: 68.431.23.4758.02

Date: 2024-03-18



				Limit	005+008	010
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	0.022
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
<b>Conclusion</b>					<b>Pass</b>	<b>Pass</b>

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)
					011
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0	%	0.005	0.1	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.
<b>Conclusion</b>					<b>Pass</b>

**Remark:**

- The test results of the sample 011 is transferred from sample 015 of report 68.431.23.4283.

Regd. Office: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch  
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998  
 Fax: +86 755 8828 5299  
 E-mail: info@tuv sud.com  
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China  
 Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



13. Bisphenol A Content

Test method: Test with reference to in house method followed by LC-MSMS analysis.

Compound	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					001^	003
Bisphenol A	80-05-7	mg/kg	0.1	0.1	N.D.	N.D.
<b>Conclusion</b>					<b>Pass</b>	<b>Pass</b>

Compound	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					004	005
Bisphenol A	80-05-7	mg/kg	0.1	0.1	N.D.	N.D.
<b>Conclusion</b>					<b>Pass</b>	<b>Pass</b>

Compound	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					008	010
Bisphenol A	80-05-7	mg/kg	0.1	0.1	N.D.	N.D.
<b>Conclusion</b>					<b>Pass</b>	<b>Pass</b>

Compound	CAS No.	Unit	MDL	Client's Limit	Result(s)
					011
Bisphenol A	80-05-7	mg/kg	0.1	0.1	N.D.
<b>Conclusion</b>					<b>Pass</b>

Remark:

1. The test results of the sample 011 is transferred from sample 015 of report 68.431.23.4283.
2. "^" denotes sample was received on 2024-03-12.

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch  
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,  
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998  
 Fax: +86 755 8828 5299  
 E-mail: info@tuvsud.com  
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



14. FDA CFR Title 21 Part 177.1210

Test for compliance with the selected requirement(s) in U.S. F.D.A. C.F.R. 21. Part 177.1210

TEST ITEMS	TEST CONDITIONS	MDL [ppm]	RESULT [ppm]	CFR Specification [ppm]
			005	
Chloroform extractives in Distilled water	Fill boiling water and then cool to 100 °F	10	N.D.	50
Chloroform extractives in 8% Ethanol	Fill boiling 8% ethanol and then cool to 100 °F	10	N.D.	50
<b>Conclusion</b>			Pass	-

Note:

1. "ppm" denotes part per million
2. "<" denotes less than
3. "°F" denotes degree Fahrenheit
4. The specification is quoted from U.S. F.D.A. C.F.R. 21. Part 177.1210

15. FDA CFR Title 21 Part 177.1520

Test for compliance with the selected requirement(s) in U.S. F.D.A. C.F.R. 21. Part 177.1520

TEST ITEMS	RESULTS	CFR Specification [PP/PE Copolymer]
	004	
Density [g/cc]	0.900	0.85 - 1.00
Maximum extractive in n-hexane 50°C for 2 hours [%]	<1.00	5.5
Maximum extractive in xylene after reflux for 2 hours and 25°C for 1 hour [%]	2.11	30
<b>Conclusion</b>	Pass	-

Note:

1. "%" denotes percentage by weight
2. "g/cc" denotes gram per cubic centimeter
3. "<" denotes less than
4. "°C" denotes degree Celsius
5. The specification is quoted from U.S. F.D.A. C.F.R. 21. Part 177.1520

Regd. Office: TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch  
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998  
 Fax: +86 755 8828 5299  
 E-mail: info@tuvsud.com  
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



16. Total Chromium Content

Test for compliance with the selected requirement(s) in the General Recognized As Safe (GRAS) specification according to United State Food and Drug Administration (US FDA) Regulations on stainless steel  
Test Method: Digested by acid and analyzed by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES)

Analyte	Results [%]
	Sample 006
Total Chromium(Cr)	17.66
Limit	Not less than 16
Conclusion	Pass

Note:

- “%” denotes percentage by weight



Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch  
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,  
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998  
Fax: +86 755 8828 5299  
E-mail: info@tuvsud.com  
Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China