



Test Report

No.: 68.431.23.4283.02

Date: 2024-01-24

Applicant: Spector & CO
Address: /
Product Name: 20 OZ/600ML DOUBLE WALL VACCUM INSULATED STAINLESS STEEL BOTTLE
End Use: DRINKWARE
Item No.: DW309
Style No.: EYE CANDY
Supplier: USS049
Country of Origin: CHINA
Country of Destination: CANADA & U.S.A.
Receipt Date of Sample: 2023-11-20, 2023-12-25, 2024-01-17
Date of Testing: From 2023-11-22 to 2024-01-24
Sample Submitted: The sample(s) was (were) submitted by applicant and identified.
Test Result: Refer to the data listed in following pages

Test Item	Conclusion
1. US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials	Pass*
2. US California Proposition 65 - Total Cadmium Content Test - Substrate Materials	Pass*
3. US California Proposition 65 - Total lead Content Test - Paint and Similar Surface-Coating Materials	Pass*
4. US California Proposition 65 - Total Lead Content Test - Substrate Materials	Pass*
5. Phthalates Content (11P)	Pass*
6. Tungsten Content Test	See Test Result
7. Canada Consumer Product Safety Act (S.C. 2010, c. 21), Surface Coating Materials Regulations SOR/2016-193 and SOR/2022-122 - Total Mercury	Pass
8. Canada Consumer Product Safety Act (S.C. 2010, c. 21), Surface Coating Materials Regulations SOR/2016-193 and SOR/2022-122 - Total Lead	Pass
9. Canadian Consumer Products Containing Lead Regulations SOR/2018-83 - Total Lead Content Test	Pass
10. Total Nickel Content Test	See Test Result
11. U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P)	Pass
12. US California Proposition 65 - Phthalates Content (6P)	Pass*
13. Bisphenol A Content	Pass*
14. FDA CFR Title 21 Part 177.1210 (Only test Chloroform extractives in Distilled water, N-heptane)	Pass
15. FDA CFR Title 21 Part 177.1520	Pass
16. Total Chromium	Pass

Regd. Office: TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: info@tuv sud.com
Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



- Remarks:
1. MDL = Method Detection Limit
 2. N.D. = Not Detected (<MDL)
 3. ≤ Less than
 4. 1 mg/kg = 1 ppm = 0.0001%
 5. NA=Not Applicable

**TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Testing Center**

Prepared by:

Authorized by:



Huang, Jessica
Senior Project Coordinator

Shu, Steven
Senior Project Coordinator

Note:

- (1) The TÜV SÜD Certification and Testing (China) Co., Ltd. "General Terms & Conditions" applied.
Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.
For further details, please see "Testing and certification regulation", chapter A-3.4
For full version, please visit: EN : <https://www.tuvsud.cn/zh-cn/resource/terms-and-conditions---en> ; SCN: <https://www.tuvsud.cn/zh-cn/terms-and-conditions> ; TCN: <https://www.tuvsud.com/zh-tw/terms-and-conditions>
- (2) The results relate only to the items tested.
- (3) The test report shall not be reproduced except in full without the written approval of the laboratory
- (4) If relevant standards do not specify decision rule(s), follow decision rule as below:
- "Pass" means that the measured result is within the limits, even when extended by expanded uncertainty at a level of confidence of 95%.
- "Fail" means that the measured result is beyond the limit, even when extended by expanded uncertainty at a level of confidence of 95%.
- (5) The test item and sample were specified by the client.
- (6) ""*"" denotes the conclusion was drawn according to the client's specification.

Regd. Office: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: info@tuvsud.com
Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China
Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Description of Tested Subject:

Sample	Description	Photo
A	Whole product	
001	Silvery 304 stainless steel (Body inner, body outer, cap of lid)	
002	Black PP homopolymer plastic (Lid)	
003	Grey silicone (Sealing ring)	

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Sample	Description	Photo
004	Black silicone with adhesive backing (Bottom)	
005	Black printed white paper sticker (QR code label)	
010	White coating (Bottle body)	
011	Sky blue coating (Dry paint)	
012	Orange coating (Dry paint)	
013	Pink coating (Dry paint)	

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com



Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Sample	Description	Photo
014	Black coating (Dry paint)	
015	rubber oil	

T. No	Sample	Description
T1	001	Silvery 304 stainless steel (Body inner, body outer, cap of lid)
T2	002	Black PP homopolymer plastic (Lid)
T3	003	Grey silicone (Sealing ring)
T4	004	Black silicone with adhesive backing (Bottom)
T5	005	Black printed white paper sticker (QR code label)
T6	010	White coating (Bottle body)
T7	011	Sky blue coating (Dry paint)
T8	012	Orange coating (Dry paint)
T9	013	Pink coating (Dry paint)
T10	014	Black coating (Dry paint)
T11	015	rubber oil

Remark: Sample 011~013, 014 were received on 2023-12-25.

Regd. Office: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuv sud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China
 Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



Test Result(s):

1. US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
010	mg/kg	10	75	N.D.	Pass
011+012+013	mg/kg	10	75	N.D.	Pass
014	mg/kg	10	75	N.D.	Pass
015	mg/kg	10	75	N.D.	Pass

2. US California Proposition 65 - Total Cadmium Content Test - Substrate Materials

Test with reference to acid digestion or microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
001	mg/kg	10	75	N.D.	Pass
002+003	mg/kg	10	75	N.D.	Pass
004	mg/kg	10	75	N.D.	Pass
005	mg/kg	10	75	N.D.	Pass

3. US California Proposition 65 - Total Lead Content Test - Paint and Similar Surface-Coating Materials

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
010	mg/kg	10	90	N.D.	Pass
011+012+013	mg/kg	10	90	N.D.	Pass
014	mg/kg	10	90	N.D.	Pass
015	mg/kg	10	90	N.D.	Pass

4. US California Proposition 65 - Total Lead Content Test - Substrate Materials

Test with reference to acid digestion or microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
001	mg/kg	10	100	N.D.	Pass
002+003	mg/kg	10	100	N.D.	Pass
004	mg/kg	10	100	N.D.	Pass
005	mg/kg	10	100	N.D.	Pass

Regd. Office: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuv sud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China
 Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



5. Phthalates Content (11P)

Test with reference to in-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS).

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					002+003	004
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuvsud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.23.4283.02

Date: 2024-01-24



Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					005	011+012+013
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					014	015
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

6. Tungsten Content Test

Test with reference to acid digestion and determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES)

Test items	Unit	MDL	Limit	Result(s)
				001
Tungsten(W)	mg/kg	10.0	-	N.D.
Conclusion				Report As Is

Regd. Office: TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuvsud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China
 Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



7. Canada Consumer Product Safety Act (S.C. 2010, c. 21), Surface Coating Materials Regulations SOR/2016-193 and SOR/2022-122 - Total Mercury

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
005	mg/kg	10	10.0	N.D.	Pass
010	mg/kg	10	10.0	N.D.	Pass
011	mg/kg	10	10.0	N.D.	Pass
012	mg/kg	10	10.0	N.D.	Pass
013	mg/kg	10	10.0	N.D.	Pass
014	mg/kg	10	10.0	N.D.	Pass
015	mg/kg	10	10.0	N.D.	Pass

8. Canada Consumer Product Safety Act (S.C. 2010, c. 21), Surface Coating Materials Regulations SOR/2016-193 and SOR/2022-122 - Total Lead

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
005	mg/kg	10	90	N.D.	Pass
010	mg/kg	10	90	N.D.	Pass
011+012+013	mg/kg	10	90	N.D.	Pass
014	mg/kg	10	90	N.D.	Pass
015	mg/kg	10	90	N.D.	Pass

9. Canadian Consumer Products Containing Lead Regulations SOR/2018-83 - Total Lead Content Test

Test with reference to acid digestion or microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
001	mg/kg	10	90	N.D.	Pass
002+003	mg/kg	10	90	N.D.	Pass
004	mg/kg	10	90	N.D.	Pass
005	mg/kg	10	90	N.D.	Pass
010	mg/kg	10	90	N.D.	Pass
011+012+013	mg/kg	10	90	N.D.	Pass
014	mg/kg	10	90	N.D.	Pass
015	mg/kg	10	90	N.D.	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuv sud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



10. Total Nickel Content Test

Test with reference to acid digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
001	mg/kg	5	-	77558.022	Report As Is

11. U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P)

Test with reference to in-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS).

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					002+003	004
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuvsud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.23.4283.02

Date: 2024-01-24



Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					005	011+012+013
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					014	015
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



12. US California Proposition 65 - Phthalates Content (6P)

Test with reference to in-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS).

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					002+003	004
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					005	011+012+013
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuvsud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					014	015
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

13. Bisphenol A Content

Test method: With reference to In house method followed by LC-MSMS analysis.

Compound	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					002	003
Bisphenol A	80-05-7	mg/kg	0.1	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Compound	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					004	005
Bisphenol A	80-05-7	mg/kg	0.1	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Compound	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					010	011
Bisphenol A	80-05-7	mg/kg	0.1	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Compound	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					012	013
Bisphenol A	80-05-7	mg/kg	0.1	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Compound	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					014	015
Bisphenol A	80-05-7	mg/kg	0.1	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



14. FDA CFR Title 21 Part 177.1210 (Only test Chloroform extractives in Distilled water, N-heptane)
 Test for compliance with the selected requirement(s) in U.S. F.D.A. C.F.R. 21. Part 177.1210

TEST ITEMS	TEST CONDITIONS	RESULT [ppm]	CFR Specification [ppm]
		SAMPLE 003	
Chloroform extractives in Distilled water	Fill boiling water and then cool to 100 °F	<10	50
Chloroform extractives in N-heptane	120 °F, 15 mins	<10	50
Conclusion		Pass	-

Note:

1. "ppm" denotes part per million
2. "<" denotes less than
3. "°F" denotes degree Fahrenheit
4. The specification is quoted from U.S. F.D.A. C.F.R. 21. Part 177.1210

15. FDA CFR Title 21 Part 177.1520

Test for compliance with the selected requirement(s) in U.S. F.D.A. C.F.R. 21. Part 177.1520

TEST ITEMS	RESULTS	CFR Specification [PP Homopolymer]
	SAMPLE 002	
Density [g/cc]	0.903	0.880 - 0.913
Melting Point Range [°C]	161-168	160 - 180
Maximum extractive in n-hexane after reflux for 2 hours [%]	<1.00	6.4
Maximum extractive in xylene after Dissolved completely at 120°C and 25°C for 1 hour [%]	5.78	9.8
Conclusion		-

Note:

1. "%" denotes percentage by weight
2. "g/cc" denotes gram per cubic centimeter
3. "<" denotes less than
4. "°C" denotes degree Celsius
5. The specification is quoted from U.S. F.D.A. C.F.R. 21. Part 177.1520

Regd. Office: TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuvsud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China
 Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



16. Total Chromium Content

Test for compliance with the selected requirement(s) in the General Recognized As Safe (GRAS) specification according to United State Food and Drug Administration (US FDA) Regulations on stainless steel

Test Method: Digested by acid and analyzed by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES)

Analyte	Results [%]
	Sample 001
Total Chromium(Cr)	18.17
Limit	Not less than 16
Conclusion	Pass

Note:

- “%” denotes percentage by weight



-End of Test Report-

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuvsud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China