



Greater China

Test Report

No.: 68.431.22.4445.01

Date: 2022-10-31

Applicant: Spector & CO
Address: /
Product Name: 400ML/ 13.5 OZ DOUBLE WALL VACCUM INSULATED STAINLESS STEEL TUMBLER/CAN & BOTTLE COOLER 3in1.
End Use:
Item No.: DW409
Style No.: GAME CHANGER 3IN1
Supplier: USS149
Country of Origin: CHINA
Country of Destination: CANADA & U.S.A.
Receipt Date of Sample: 2022-10-18
Date of Testing: From 2022-10-18 to 2022-10-27
Sample Submitted: The sample(s) was (were) submitted by applicant and identified.
Test Result: Refer to the data listed in following pages

Test Item	Conclusion
1. US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials	Pass*
2. US California Proposition 65 - Total Cadmium Content Test - Substrate Materials	Pass*
3. US California Proposition 65 - Total lead Content Test - Paint and Similar Surface-Coating Materials	Pass*
4. US California Proposition 65 - Total Lead Content Test - Substrate Materials	Pass*
5. Phthalates Content (11P)	Pass*
6. Tungsten Content Test	Report As Is
7. Canadian Surface Coating Materials Regulations SOR/2016-193 - Total Mercury Content Test	Pass
8. Canadian Surface Coating Materials Regulations SOR/2016-193 - Total Lead Content Test	Pass
9. Canadian Consumer Products Containing Lead Regulations SOR/2018-83 - Total Lead Content Test	Pass
10. Total Nickel Content Test	Report As Is
11. U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P)	Pass
12. US California Proposition 65 - Phthalates Content (6P)	Pass*
13. FDA CFR Title 21 Part 181.32	Pass
14. FDA CFR Title 21 Part 177.1210	Pass
15. Total Chromium	Pass

Remarks: 1. MDL = Method Detection Limit
2. N.D. = Not Detected (<MDL)
3. ≤ Less than
4. 1 mg/kg = 1 ppm = 0.0001%
5. NA=Not Applicable

Regd. Office: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: info@tuvsud.com
Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.22.4445.01

Date: 2022-10-31



Greater China

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Testing Center

Prepared by:

Authorized by:

Jojo Zhao



Steven Shu

Jojo Zhao
Project Coordinator

Shu, Steven
Senior Project Coordinator

Note:

- (1) The TÜV SÜD Certification and Testing (China) Co., Ltd. "General Terms & Conditions" applied.
Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.
For further details, please see "Testing and certification regulation", chapter A-3.4
For full version, please visit: EN : <https://www.tuvsud.cn/zh-cn/resource/terms-and-conditions---en> ; SCN: <https://www.tuvsud.cn/zh-cn/terms-and-conditions> ; TCN: <https://www.tuvsud.com/zh-tw/terms-and-conditions>
- (2) The results relate only to the Items tested.
- (3) The test report shall not be reproduced except in full without the written approval of the laboratory
- (4) If relevant standards do not specify decision rule(s), follow decision rule as below:
- "Pass" means that the measured result is within the limits, even when extended by expanded uncertainty at a level of confidence of 95%.
- "Fail" means that the measured result is beyond the limit, even when extended by expanded uncertainty at a level of confidence of 95%.
- (5) The test item and sample were specified by the client.
- (6) "*" denotes the conclusion was drawn according to the client's specification.

Regd. Office:

Tüv Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : <http://www.tuvsud.cn>


Lab 1 - Chemical testing and part of
electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Description of Tested Subject:

Sample	Description	Photo
A	Whole product	
001	Transparent AS plastic (Lid & sliding cover)	
002	Translucent white silicone (Stopper on lid)	
003	Black silicone (Sealing ring)	

Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

<p>004</p>	<p>Matt-black silicone (Base pad)</p>	
<p>005</p>	<p>Yellow coating (On body)</p>	
<p>006</p>	<p>Orange coating (On body)</p>	
<p>007</p>	<p>Purple coating (On body)</p>	
<p>008</p>	<p>Green coating (On body)</p>	

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

009	Black coating (On body)			
010	Red coating (On body)			
011	Blue coating (On body)			
012	Bright black silicone (Case)			
013	Yellow silicone (Case)			
014	Red silicone (Case)			
015	Green silicone (Case)			
016	Purple silicone (Case)			
017	Blue silicone (Case)			
018	Orange silicone (Case)	019	Silver stainless steel 304 (Inner body)	
020	Silver stainless steel 201 (Outer body)			

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.22.4445.01

Date: 2022-10-31



Greater China

T. No	Sample	Description
T1	001	Transparent AS plastic (Lid & sliding cover)
T2	002	Translucent white silicone (Stopper on lid)
T3	003	Black silicone (Sealing ring)
T4	004	Matt-black silicone (Base pad)
T5	005	Yellow coating (On body)
T6	006	Orange coating (On body)
T7	007	Purple coating (On body)
T8	008	Green coating (On body)
T9	009	Black coating (On body)
T10	010	Red coating (On body)
T11	011	Blue coating (On body)
T12	012	Bright black silicone (Case)
T13	013	Yellow silicone (Case)
T14	014	Red silicone (Case)
T15	015	Green silicone (Case)
T16	016	Purple silicone (Case)
T17	017	Blue silicone (Case)
T18	018	Orange silicone (Case)
T19	019	Silver stainless steel 304 (Inner body)
T20	020	Silver stainless steel 201 (Outer body)

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of
electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



Test Result(s):

1. US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
005+006+007	mg/kg	10	75	N.D.	Pass
008+009+010	mg/kg	10	75	N.D.	Pass
011	mg/kg	10	75	N.D.	Pass

2. US California Proposition 65 - Total Cadmium Content Test - Substrate Materials

Test with reference to acid digestion or microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
001+002+003	mg/kg	10	75	N.D.	Pass
004+012+013	mg/kg	10	75	N.D.	Pass
014+015+016	mg/kg	10	75	N.D.	Pass
017+018	mg/kg	10	75	N.D.	Pass
019	mg/kg	10	75	N.D.	Pass
020	mg/kg	10	75	N.D.	Pass

3. US California Proposition 65 - Total Lead Content Test - Paint and Similar Surface-Coating Materials

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
005+006+007	mg/kg	10	90	N.D.	Pass
008+009+010	mg/kg	10	90	N.D.	Pass
011	mg/kg	10	90	N.D.	Pass

4. US California Proposition 65 - Total Lead Content Test - Substrate Materials

Test with reference to acid digestion or microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
001+002+003	mg/kg	10	100	N.D.	Pass
004+012+013	mg/kg	10	100	N.D.	Pass
014+015+016	mg/kg	10	100	N.D.	Pass
017+018	mg/kg	10	100	N.D.	Pass
019	mg/kg	10	100	N.D.	Pass
020	mg/kg	10	100	N.D.	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

5. Phthalates Content (11P)

Test with reference to in-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS).

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					001+002+003	004+012+013
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					005+006+007	008+009+010
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.22.4445.01

Date: 2022-10-31



Greater China

Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					011	014+015+016
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)
					017+018
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.

Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuv sud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.22.4445.01

Date: 2022-10-31



Greater China

Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.
Conclusion					Pass

6. Tungsten Content Test

Test with reference to acid digestion and determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES)

Test items	Unit	MDL	Limit	Result(s)
				020
Tungsten(W)	mg/kg	10.0	-	N.D.
Conclusion				Report As Is

7. Canadian Surface Coating Materials Regulations SOR/2016-193 - Total Mercury Content Test

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
005	mg/kg	10	10.0	N.D.	Pass
006	mg/kg	10	10.0	N.D.	Pass
007	mg/kg	10	10.0	N.D.	Pass
008	mg/kg	10	10.0	N.D.	Pass
009	mg/kg	10	10.0	N.D.	Pass
010	mg/kg	10	10.0	N.D.	Pass
011	mg/kg	10	10.0	N.D.	Pass

8. Canadian Surface Coating Materials Regulations SOR/2016-193 - Total Lead Content Test

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
005+006+007	mg/kg	10	90	N.D.	Pass
008+009+010	mg/kg	10	90	N.D.	Pass
011	mg/kg	10	90	N.D.	Pass

9. Canadian Consumer Products Containing Lead Regulations SOR/2018-83 - Total Lead Content Test

Test with reference to acid digestion or microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuv sud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.22.4445.01

Date: 2022-10-31



Greater China

Sample	Unit	MDL	Limit	Result(s)	Conclusion
001+002+003	mg/kg	10	90	N.D.	Pass
004+012+013	mg/kg	10	90	N.D.	Pass
005+006+007	mg/kg	10	90	N.D.	Pass
008+009+010	mg/kg	10	90	N.D.	Pass
011	mg/kg	10	90	N.D.	Pass
014+015+016	mg/kg	10	90	N.D.	Pass
017+018	mg/kg	10	90	N.D.	Pass
019	mg/kg	10	90	N.D.	Pass
020	mg/kg	10	90	N.D.	Pass

10. Total Nickel Content Test

Test with reference to acid digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
019	mg/kg	5	-	77414.562	Report As Is
020	mg/kg	5	-	54419.890	Report As Is

11. U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P)

Test with reference to in-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS).

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					001+002+003	004+012+013
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					005+006+007	008+009+010

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.22.4445.01

Date: 2022-10-31



Greater China

Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					011	014+015+016
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Limit	Result(s)
					017+018
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.22.4445.01

Date: 2022-10-31



Greater China

Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.
Conclusion					Pass

12. US California Proposition 65 - Phthalates Content (6P)

Test with reference to in-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS).

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					001+002+003	004+012+013
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					005+006+007	008+009+010
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Client's	Result(s)
-----------	---------	------	-----	----------	-----------

Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.22.4445.01

Date: 2022-10-31



Greater China

				Limit	011	014+015+016
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)
					017+018
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.
Conclusion					Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



13. FDA CFR Title 21 Part 181.32

Test for compliance with the selected requirement(s) in U.S. F.D.A. C.F.R. 21. Part 180.22 & 181.32

SIMULANT USED	TEST CONDITIONS	RESULT [mg/in ²]	CFR Specification [mg/in ²]
		SAMPLE 001	
Distilled Water	100 °C for 0.5 Hour	<0.001	0.003
3% Acetic acid	100 °C for 0.5 Hour	<0.001	0.003
8% ethanol	100 °C for 0.5 Hour	<0.001	0.003
n-heptane	49 °C for 0.5 Hour	<0.001	0.003
50% Ethanol	100 °C for 0.5 Hour	<0.001	0.003
Conclusion		Pass	-

Note:

1. "mg/in²" denotes milligram per square inch
2. "<" denotes less than
3. "°C" denotes degree Celsius
4. The specification is quoted from U.S. F.D.A. C.F.R. 21. Part 180.22 & 181.32

14. FDA CFR Title 21 Part 177.1210

Test for compliance with the selected requirement(s) in U.S. F.D.A. C.F.R. 21. Part 177.1210

TEST ITEMS	TEST CONDITIONS	RESULT [ppm]	CFR Specification [ppm]
		SAMPLE 003	
Chloroform extractives in Distilled water	100 °C for 0.5 Hour	<10.0	50
Chloroform extractives in 8% Ethanol	100 °C for 0.5 Hour	<10.0	50
Chloroform extractives in N-heptane	49 °C for 0.5 Hour	10.9	250
Conclusion		Pass	-

Note:

1. "ppm" denotes part per million
2. "<" denotes less than
3. "°C" denotes degree Celsius
4. The specification is quoted from U.S. F.D.A. C.F.R. 21. Part 177.1210



15. Total Chromium Content


Test for compliance with the selected requirement(s) in the General Recognized As Safe (GRAS) specification according to United State Food and Drug Administration (US FDA) Regulations on stainless steel

Test Method: Digested by acid and analyzed by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES)

Analyte	Results [%]
	Sample 019
Total Chromium(Cr)	17.75
Limit	Not less than 16
Conclusion	Pass

Note:

- “%” denotes percentage by weight



Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuvsud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China