

TEST REPORT

Test Report # 21W-010975 Date of Report Issue: August 17, 2021
Date of Sample Received: July 7, 2021 Pages: Page 1 of 25

CLIENT INFORMATION:

Company: Spector & Co.
Address: -



SAMPLE INFORMATION:

Description: REUSABLE FACE MASK BLACK WITH WIRED NOSEPIECE
Assortment: BAMBOO ECO
Model/style No.: EC913
PO No.: -
SKU No.: -
Item No./Item Name: -
Factory/Supplier: USY018
Country of Origin: China
Country of Distribution: Canada, United States
Testing Period: 07/09/2021-07/16/2021, 07/22/2021-07/28/2021, 08/10/2021-08/10/2021

OVERALL RESULT:

PASS with information

Please refer to the following pages for test result summary and appropriate notes.

QIMA (HANGZHOU) TESTING CO., LTD.

QIMA (HANGZHOU) TESTING CO., LTD.



Jeremy Xu
Chemical Laboratory Supervisor

Aiden Xu
Textile Laboratory Supervisor



QIMA (HANGZHOU) TESTING CO., LTD. ♦ 4-5/F A2 BLDG NO. 1213 HUOJU SOUTH ROAD PUYAN STREET BINJIANG DISTRICT HANGZHOU CHINA

♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the [QIMA decision rule](#).

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	California Proposition 65, Total Lead in Substrate Materials
Not Applicable	Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead and Mercury in Paints and Surface Coatings
PASS	Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content
PASS	California Proposition 65, Total Cadmium in Substrate Materials
Not Applicable	Client's requirement, Total Nickel content
PASS	CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)
PASS	Client's Requirement, Phthalates content
PASS	Appearance after Laundering
Information only	Color Fastness to Washing
PASS	Color Fastness to Crocking
Information only	Color Fastness to Perspiration
PASS	Flammability Test of Clothing Textiles
Information only	Fiber Content
Information only	R.S.C, 1985 c. T-10 / C.R.C. c. 1551-Textile Labeling Act / Textile Labelling and Advertising Regulations-Fiber Content Verification
Information only	16 CFR 303-Textiles-Labeling Review (Fiber Content)
Information only	16 CFR 423-Textiles-Labeling Review (Care Label)
Information only	R.S.C, 1985 c. T-10 / C.R.C. c. 1551-Textile Labeling Act / Textile Labelling and Advertising Regulations-Labeling Review (Fiber Content)
PASS	CANADA-Textiles-Labeling Review (Care Label)



DETAILED RESULTS:

California Proposition 65, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3	4	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	---	---	100
Conclusion	PASS	PASS	PASS	---	---	

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit =15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



DETAILED RESULTS:

Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	3	4	---	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	---	---	---	90
Conclusion	PASS	PASS	---	---	---	

Note:

mg/kg=Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)



DETAILED RESULTS:

California Proposition 65, Total Cadmium in Substrate Materials

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3	4	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Cadmium (Cd)	ND	ND	ND	---	---	75
Conclusion	PASS	PASS	PASS	---	---	

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



DETAILED RESULTS:

CPSC 16 CFR 1307 Prohibition of Children’s Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method: CPSC-CH-C1001-09.4
 Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		3	4	---	---	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	---	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	---	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	---	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	---	---	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	---	---	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	---	---	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	---	---	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	---	---	1000
Conclusion		PASS	PASS	---	---	

Note:
 mg/kg = Milligrams per kilogram
 LT = Less than
 ND = Not detected (Reporting Limit = 150 mg/kg)



DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.4
 Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1+2	3	4	---	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	---	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	---	1000
Conclusion		PASS	PASS	PASS	---	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)
 LT = Less than
 ND = Not detected (Reporting Limit = 150 mg/kg)
 Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



DETAILED RESULTS:

Client's Requirement, Phthalates content

Test Method: CPSC-CH-C1001-09.4
 Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1+2	3	4	---	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	---	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	---	1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	ND	ND	---	1000
Diethyl phthalate (DEP)	84-66-2	ND	ND	ND	---	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	---	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	---	1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND	ND	ND	---	1000
Conclusion		PASS	PASS	PASS	---	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



DETAILED RESULTS:

Appearance after Laundering

Test Method: IHTM-TXHZ-002, observations on 3 cycles washed sample.

Specimen No.	1		
Assessing Items	Observation	Requirement	Result
Color Change	Negligible Change (Grade 4.5)	Min. 4.0	PASS
Pilling/fuzzing	Negligible Change (Grade 4.5)	Min. 3.5	PASS
Fabric Appearance	Negligible Change	No break, no noticeable crease / Snagging	PASS
Conclusion	PASS		

Specimen No.	2		
Assessing Items	Observation	Requirement	Result
Color Change	Negligible Change (Grade 4.5)	Min. 4.0	PASS
Pilling/fuzzing	Negligible Change (Grade 4.5)	Min. 3.5	PASS
Fabric Appearance	Negligible Change	No break, no noticeable crease / Snagging	PASS
Conclusion	PASS		

Remark:

- (1) Grey scale rating is based on the 5-step of 1 to 5, where 1 is bad and 5 is good.
- (2) Washing procedure: AATCC TS-006: Hand wash at 105 °F, hang dry.



DETAILED RESULTS:

Appearance after Laundering

Test Method: IHTM-TXHZ-002, observations on 3 cycles washed sample.

Specimen No.	5		
Assessing Items	Observation	Requirement	Result
Color Change	Negligible Change (Grade 4.5)	Min. 4.0	PASS
Pilling/fuzzing	Negligible Change (Grade 4.5)	Min. 3.5	PASS
Fabric Appearance	Negligible Change	No break, no noticeable crease / Snagging	PASS
Conclusion	PASS		

Remark:

- (1) Grey scale rating is based on the 5-step of 1 to 5, where 1 is bad and 5 is good.
- (2) Washing procedure: AATCC TS-006: Hand wash at 105 °F, hang dry.



DETAILED RESULTS:

Color Fastness to Washing

Test Method: AATCC 61-2013; Test No. 1A, Machine wash at 105 degree F with 0.37% '1993 AATCC standard reference detergent WOB' with 10 steel balls.

Specimen No.	1	2	---	---	---	Client's requirement
Items	Result (Grade)	Result (Grade)	Result (Grade)	Result (Grade)	Result (Grade)	
Change in shade	4.5	4.5	---	---	---	N/A
Staining on multi-fiber stripe						
-Acetate	4.5	4.5	---	---	---	N/A
-Cotton	4.5	4.5	---	---	---	N/A
-Nylon	4.5	4.5	---	---	---	N/A
-Polyester	4.5	4.5	---	---	---	N/A
-Acrylic	4.5	4.5	---	---	---	N/A
-Wool	4.5	4.5	---	---	---	N/A
Conclusion	Information only	Information only	---	---	---	-

Remark: Grey scale rating is based on the 5-step of 1 to 5, where 1 is bad and 5 is good.

Color Fastness to Crocking

Test Method: AATCC 8-2016

Specimen No.	1	2	---	---	---	Client's requirement
Items	Result (Grade)	Result (Grade)	Result (Grade)	Result (Grade)	Result (Grade)	
Dry staining	4.5	4.5	---	---	---	Min 4.0
Wet staining	4.0	3.5	---	---	---	Min 2.5
Conclusion	PASS	PASS	---	---	---	-

Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.



DETAILED RESULTS:

Color Fastness to Perspiration

Test Method: AATCC 15-2013(E2014)

Specimen No.	1	2	---	---	---	Client's requirement
Items	Acidic Result (Grade)	Acidic Result (Grade)	Acidic Result (Grade)	Acidic Result (Grade)	Acidic Result (Grade)	
Change in shade	4.5	4.5	---	---	---	N/A
Staining on multi-fiber stripe						
-Acetate	4.5	4.5	---	---	---	N/A
-Cotton	4.5	4.5	---	---	---	N/A
-Nylon	4.5	4.5	---	---	---	N/A
-Polyester	4.5	4.5	---	---	---	N/A
-Acrylic	4.5	4.5	---	---	---	N/A
-Wool	4.5	4.5	---	---	---	N/A
Conclusion	Information only	Information only	---	---	---	-

Remark: Grey scale rating is based on the 5-step of 1 to 5, where 1 is bad and 5 is good.

Flammability Test of Clothing Textiles

Test Method: 16 CFR Part 1610

Specimen No.	1	
Items	Result	Client's requirement
Specific exemptions	After testing, fabric weight of sample is >2.6 oz / sq. yd. Thus the sample is exempt from flammability testing in accordance with 16 CFR 1610.1(d)(1): Plain surface fabric with fabric weight ≥ 2.6 oz/sq. yd.	Class I
Conclusion	EXEMPT	



DETAILED RESULTS:

Flammability Test of Clothing Textiles

Test Method: 16 CFR Part 1610

Specimen No.	2				
Preliminary Tests	<u>Fabric Surface</u>	Smooth	<u>Test Specimen Direction</u>		Face Length
Items	Result				Client's requirement
	<u>As Received</u>		<u>After Dry-cleaning and Laundering*</u>		
	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	
(1)	-	DNI	-	DNI	Class I
(2)	-	DNI	-	DNI	
(3)	-	DNI	-	DNI	
(4)	-	DNI	-	DNI	
(5)	-	DNI	-	DNI	
Flammability Classification	Class I				
Conclusion	PASS				

Remarks

Class 1 Normal Flammability
 Class 1 textiles exhibit normal flammability and are acceptable for use in clothing.

* Drycleaning / Laundering procedure is according to 16 CFR 1610:6(b).

Burn Code Description:

DNI = Did not ignite



DETAILED RESULTS:

Fiber Content

Test Method: AATCC 20-2018/AATCC 20A-2018; based on moisture regain weight.

Specimen No.	1		
Items	Client's requirement	Result	Conclusion
Rayon (%)	N/A	53.0	Information only
Polyester (%)	N/A	47.0	

Note:

(1) Exclusive of trimming.

(2) Based on ASTM D1909-13, Moisture regain of Rayon: 11.0%, Polyester: 0.4%.

Fiber Content

Test Method: AATCC 20-2018

Specimen No.	2		
Items	Client's requirement	Result	Conclusion
Cotton (%)	100	100	PASS



DETAILED RESULTS:

**R.S.C, 1985 c. T-10 / C.R.C. c. 1551-Textile Labeling Act / Textile Labelling and Advertising Regulations-
Fiber Content Verification**

Test Method: CAN/CGSB-4.2 No. 14-2005; based on moisture regain weight.

Specimen No.	1		
Items	Client's requirement	Result	Conclusion
Rayon (%)	N/A	53.0	Information only
Polyester (%)	N/A	47.0	

Note:

- (1) Exclusive of trimming
- (2) Based on CAN/CGSB 4.2 No.0-2001, Moisture regain of Rayon: 11.0%, Polyester: 0.4%.

**R.S.C, 1985 c. T-10 / C.R.C. c. 1551-Textile Labeling Act / Textile Labelling and Advertising Regulations-
Fiber Content Verification**

Test Method: CAN/CGSB-4.2 No. 14-2005.

Specimen No.	2		
Items	Client's requirement	Result	Conclusion
Cotton (%)	100	100	PASS



DETAILED RESULTS:

16 CFR 303-Textiles-Labeling Review (Fiber Content)

Test Method: Visual Check

Test Parameters	Observation	Result
1. Fiber Content		
Percentages and generic name of all fibers that comprise 5% or more of the fiber weight must be disclosed, but if the fibers of less than 5% by weight, it should apply to 5% rule and exceptions as following: a. Fibers of less than 5% should be disclosed as “other fiber” or “other fibers” and not by their generic name or fiber trademark b. Labels must disclose wool or recycled wool by name and percentage weight, even if it is less than 5% of the product. c. Labels may state the name and percentage of a fiber that is less than 5% of the product, if the fiber has a definite functional significance at that amount.	The lab can't tell if it's recycled rayon and bamboo.	Information only
Size and conspicuousness All parts of the required fiber content information must appear in immediate proximity to each other and in type or lettering of equal size and conspicuousness.	Comply with the requirement	PASS
2. Country of origin Products must be labeled to show the country of origin.	Comply with the requirement	PASS
3. RN# or Company Name Labels must identify either the company name or the Registered Identification Number (RN) of the manufacturer, importer or another firm marketing, distributing or otherwise handling the product.	Comply with the requirement	PASS
4. Mechanics of Labeling: The above required information must be:		
Presented at Point-of-sale All parts of the required information must be clearly legible, conspicuous and readily accessible to the consumer. For packaged products except packaged hosiery product (e.g. T-shirts), the required information must be on each item in the package and on the package. If the package is transparent and consumers can read the required information on the labels without opening the package, the package doesn't need to be labeled.	Comply with the requirement	PASS



Test Parameters	Observation	Result
Permanent Label(s) with required information must be securely attached to the product until it is delivered to the consumer, but they don't need to be permanently attached.	The labeling review was based on the artwork	Information only
Language Disclosures must be in English. They can also be in other languages, as long as the English version is included.	Comply with the requirement	PASS
Conclusion	Information only	



DETAILED RESULTS:

16 CFR 423-Textiles-Labeling Review (Care Label)

Test Method: Visual Check

Test Parameters	Observation	Result
1. Care label must be sewn or affixed to the products in permanently. If label is not visible through package, care label must be repeated on a hang tag, or package, or in some other conspicuous place.	The labeling review was based on the artwork	Information only
2. Any item of textile wearing apparel, without pockets, that is totally reversible (i.e., the product is designed to be used with either side as the outer part or face) is exempt from the care label requirement. However, the required care information still must be given, and the care information can be put on a hang tag, on the package, or in some other conspicuous place, so that consumers will be able to see the care information before buying the product.	N/A	N/A
3. labels for textile wearing apparel must have either a washing instruction or a drycleaning instruction. If an item can be washed or drycleaned, the label needs only one of these instructions. If the product cannot be cleaned by any available cleaning method without being harmed, the label must so state.	Comply with the requirement	PASS
4. If a washing instruction is included, A minimum washing instruction would include a method of washing and a method of drying.	Comply with the requirement	PASS
5. If a drycleaning instruction is included, it must also state at least one type of solvent that may be used. However, if all commercially available types of solvent can be used, the label need not mention any types of solvent. The terms "Drycleanable" or "Commercially Dryclean" may not be used.	N/A	N/A
6. Certain piece goods must provide care information clearly and conspicuously on the end of each bolt or roll. Care information on the end of the bolt need only address information applicable to the fabric.	N/A	N/A
7. Detailed writing care instructions or symbol must comply to regulations for terminology, it may be contain the following information: -Washing instruction -Bleaching instruction -Drying instruction -Ironing instruction -Dry cleaning instruction	Comply with the requirement	PASS



QIMA (HANGZHOU) TESTING CO., LTD. ♦ 4-5/F A2 BLDG NO. 1213 HUOJU SOUTH ROAD PUYAN STREET BINJIANG DISTRICT HANGZHOU CHINA

♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

Test Parameters	Observation	Result
- Warning instruction (if applicable)		
Conclusion	Information only	

Remark:

- (1) N/A = Not applicable
- (2) Only the information is checked on the care label.



DETAILED RESULTS:

R.S.C, 1985 c. T-10 / C.R.C. c. 1551-Textile Labeling Act / Textile Labelling and Advertising Regulations- Labeling Review (Fiber Content)

Test Method: R.S.C., 1985, c. T-10& C.R.C., c. 1551, Visual Check.

Test Parameters	Observation	Result
1.Fibre Content		
Every fibre which is present in an amount of 5 percent or more by mass must be declared on the label using its generic name. Exceptions apply where the article contains unknown or undetermined fibres. Additional requirements apply when reclaimed fibres are present. And if the textile article contains trimming or findings other labelling requirements or alternatives exist.	The lab can't tell if it's recycled rayon and bamboo.	Information only
Every fibre which is present in an amount of less than 5 percent by mass must be declared on the label using its generic name or the term, "other fibre". Special exceptions to this requirement exist for elastic yarns, reinforcement yarns and ornamentation.	Comply with the requirement	PASS
In conjunction with the generic name, the amount of each fibre must be declared on the label as a percentage of the total fibre mass of the article or its components	Comply with the requirement	PASS
If the textile article consists of parts or sections differing in fibre content, each part or section must be declared on the label in a sectional disclosure. Sectional disclosures are also required for paddings or fillings, such as those used in pillows for beds or those added for warmth, linings and interlinings, as well as for carpets, fabric supported foams and pile, coated or impregnated fabrics.	Comply with the requirement	PASS
2. Bilingual Requirement		
All fibre content information on the label must be bilingual, except in areas where only one official language is used in consumer transactions	Comply with the requirement	PASS
3. Dealer Identity		
The dealer identity (business name and address) must be displayed on the label. Alternatively, a dealer in Canada may use a CA identification number.	Comply with the requirement	PASS
4. Country Of Origin		
If the article or any fabric or fibre therein is imported, Country of origin must be displayed on the label.	Comply with the requirement	PASS



QIMA (HANGZHOU) TESTING CO., LTD. ♦ 4-5/F A2 BLDG NO. 1213 HUOJU SOUTH ROAD PUYAN STREET BINJIANG DISTRICT HANGZHOU CHINA

♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision for stating conformity is based on the QIMA decision rule.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

Test Parameters	Observation	Result
5. Form And Application Of Labels		
The form of a label must ensure that the information contained on the label is factual, legible and accessible to the prospective consumer at the time of purchase.	The lab can't tell if it's recycled rayon and bamboo.	Information only
Depending on the type of article being labelled, either a permanent or non-permanent label must be applied to a consumer textile article. Special requirements exist for prepackaged articles and labelling alternatives exist for home-crafted articles. Exceptions to this requirement exist for custom-made articles, such as a tailored suit or a carpet cut to the customer's specification.	The labeling review was based on the artwork	Information only
Conclusion		Information only



QIMA (HANGZHOU) TESTING CO., LTD. ♦ 4-5/F A2 BLDG NO. 1213 HUOJU SOUTH ROAD PUYAN STREET BINJIANG DISTRICT HANGZHOU CHINA

♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

DETAILED RESULTS:

CANADA-Textiles-Labeling Review (Care Label)

Test Method: Visual Check

Test Parameters	Observation	Result
The provision for care information in the form of either written words or symbols (Canadian, ASTM or International) is not mandatory. However, in accordance with Section 5 of the Act, where care information is provided, the information must appear in a manner which is neither false or misleading and must accurately reflect an appropriate method of care for the article to which it applies.	Comply with the requirement	PASS
Written care instructions may be provided in English or French.	Comply with the requirement	PASS
It should be noted, however, that the Province of Quebec has additional requirements concerning the use of the French language. Information on these requirements may be obtained from l'Office québécois de la langue française.	Comply with the requirement	PASS
Conclusion	PASS	

Remark: Only the information is checked on the care label.



SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Black textile	Raw material (shell)
2	Black textile	Raw material (lining)
3	Black elastic	Elastic
4	Black soft plastic	Adjustable buckle
5	Black strap	Raw material



QIMA (HANGZHOU) TESTING CO., LTD. ♦ 4-5/F A2 BLDG NO. 1213 HUOJU SOUTH ROAD PUYAN STREET BINJIANG DISTRICT HANGZHOU CHINA

♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

SAMPLE PHOTO:



QIMA (HANGZHOU) TESTING CO., LTD. ♦ 4-5/F A2 BLDG NO. 1213 HUOJU SOUTH ROAD PUYAN STREET BINJIANG DISTRICT HANGZHOU CHINA

♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158.


Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

The following photo was provided by client, only for reference.



-End Report-

