

Test report





Overall result

Please refer to the following pages for test result summary and notes.

Client information

Client: SPECTOR & CO. Address: 5700 rue Kieran, Montréal, Quebec H4S 2B5 Canada



PASS with information

Sample information

Description:	LARA
Assortment:	BLK/BLU/GRN/ORG/RED/SLV/WHT
Item no./name:	G1103
Item class:	Writing Instrument
Country of origin:	China
Country of distribution:	Canada, United States
Quantity submitted:	3 pcs per color

General information

Sample receipt date: 07-Dec-2023 Testing period: 07-Dec-2023 to 13-Dec-2023 Purchase order #: -Factory/supplier: USY007 Labeled age grade: -Tested age grade: -

Report date: 13-Dec-2023

QIMA (Hangzhou) Testing Co., Ltd.

oremy. Xu

Jeremy Xu Chemical Laboratory Supervisor





Result summary

At the request of the client, the following test were conducted:

Test(s) conducted	Conclusion
California Proposition 65, Total Lead in Paints and Surface Coatings	PASS
California Proposition 65, Total Lead in Substrate Materials	PASS
Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead in Stickers, Films and Surface Coating Materials	PASS
Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content	PASS
California Proposition 65, Total Cadmium in Paints and Surface Coatings	PASS
California Proposition 65, Total Cadmium in Substrate Materials	PASS
Canadian Surface Coating Materials Regulations SOR/2016-193, Total Mercury in Paints and Surface Coatings	PASS
Client's requirement, Total Nickel content	Information only
Client's Requirement, Total Tungsten content	Information only
CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)	PASS
California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)	PASS
Client's Requirement, Phthalates content	PASS





California Proposition 65, Total Lead in Paints and Surface Coatings

Test Method:CPSC-CH-E1003-09.1Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	6	9+10+11	12+13	14+15		Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	ND		90
Conclusion	PASS	PASS	PASS	PASS		

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Specimen No	Transferre	Data of Issue	
Specimen No.	Report No.	Specimen No.	Date of Issue
6	23W-017860	6	13-Dec-2023





California Proposition 65, Total Lead in Substrate Materials

Test Method:CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4	5	7	8+16	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	36	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit =15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Creasimon No	Tr	Transferred from		
Specimen No.	Report No.	Specimen No.	Date of Issue	
1+2+3	23W-017860	1+2+3	13-Dec-2023	
4	23W-017860	4	13-Dec-2023	
5	23W-017860	5	13-Dec-2023	





Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead in Stickers, Films and Surface Coating Materials

Test Method:	ASTM F963-17 Clause 8.3.1
Analytical Method:	Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	6	9+10+11	12+13	14+15		Total
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Limit (mg/kg)
Total Lead (Pb)	ND	ND	ND	ND		90
Conclusion	PASS	PASS	PASS	PASS		

Note:

mg/kg=Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit =15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Specimen No	Transferre	Data of Issue	
Specimen No.	Report No.	Specimen No.	Date of Issue
6	23W-017860	6	13-Dec-2023





Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content

	ASTM F963-17 Clause 8.3.1 Inductively Coupled Plasma-Optical Emission Spectrometry					
Specimen No.	1+2+3	4	5	6	7	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	36	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	8+16	9+10+11	12+13	14+15		Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	ND		90
Conclusion	PASS	PASS	PASS	PASS		

Note:

mg/kg=Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Specimen No.	Transferre	Date of Issue	
	Report No.	Specimen No.	Date of issue
1+2+3	23W-017860	1+2+3	13-Dec-2023
4	23W-017860	4	13-Dec-2023
5	23W-017860	5	13-Dec-2023
6	23W-017860	6	13-Dec-2023





California Proposition 65, Total Cadmium in Paints and Surface Coatings

Test Method:ASTM F963-17 Clause 8.3.1Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	6	9+10+11	12+13	14+15		Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND	ND	ND	ND		75
Conclusion	PASS	PASS	PASS	PASS		

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Specimen No.	Transferre	Data of Issue		
	Report No.	Specimen No.	Date of Issue	
	6	23W-017860	6	13-Dec-2023





California Proposition 65, Total Cadmium in Substrate Materials

Test Method:ASTM F963-17 Clause 8.3.1Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4	5	7	8+16	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND	ND	ND	ND	ND	75
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Specimen No.	Transferre	ed from	Data of Issue	
	Report No.	Specimen No.	Date of Issue	
1+2+3	23W-017860	1+2+3	13-Dec-2023	
4	23W-017860	4	13-Dec-2023	
5	23W-017860	5	13-Dec-2023	





Canadian Surface Coating Materials Regulations SOR/2016-193, Total Mercury in Paints and Surface Coatings

Test Method:ASTM F963-17 Clause 8.3.1Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	6	9+10+11	12+13	14+15		Total
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Limit (mg/kg)
Total Mercury (Hg)	ND	ND	ND	ND		10
Conclusion	PASS	PASS	PASS	PASS		

Note:

mg/kg=Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 10 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Specimen No.	Transferre	Data of Issue	
	Report No.	Specimen No.	Date of Issue
6	23W-017860	6	13-Dec-2023





Client's requirement, Total Nickel content

Test Method:US EPA 3052:1996 & US EPA 6010D:2014Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4+5	7				Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Nickel (Ni)	835	21361				NA
Conclusion	Information only	Information only				

Note:

mg/kg = Milligrams per kilogram

ND = Not detected (report limit = 30 mg/kg)

NA = Not applicable

Composite results are based on specimen of least mass resulting in highest potential concentration.

Specimen No.	Transferre	Data of Issue	
	Report No.	Specimen No.	Date of Issue
4+5	23W-017860	4+5	13-Dec-2023





Client's Requirement, Total Tungsten content

Test Method:US EPA 3052:1996 & US EPA 6010D:2014Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4+5	7				Limit
Test Item	Result	Result	Result	Result	Result	(mg/kg)
	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(
Total Tungsten (W)	118	ND				NA
Conclusion	Information	Information				
	only	only				

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

NA = Not applicable

Composite results are based on specimen of least mass resulting in highest potential concentration.

Specimen No.	Transferre	Data of Issue	
	Report No.	Specimen No.	Date of Issue
4+5	23W-017860	4+5	13-Dec-2023





CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method:	CPSC-CH-C1001-09.4
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen N	0.	1+2+3	6	8+16	9+10+11	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	174	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusior	1	PASS	PASS	PASS	PASS	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Specimen No	Transferre	Data of Issue		
Specimen No.	Report No.	Specimen No.	Date of Issue	
1+2+3	23W-017860	1+2+3	13-Dec-2023	
6	23W-017860	6	13-Dec-2023	





CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method:	CPSC-CH-C1001-09.4
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen N	0.	12+13	14+15			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND			1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND			1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND			1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND			1000
Conclusior	ı	PASS	PASS			

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.





California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method:CPSC-CH-C1001-09.4Analytical Method:Gas Chromatography with Mass Spectrometry

Specimen No.		1+2+3	6	8+16	9+10+11	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	174	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusior	1	PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Specimen No	Transferre	Data of Issue		
Specimen No.	Report No.	Specimen No.	Date of Issue	
1+2+3	23W-017860	1+2+3	13-Dec-2023	
6	23W-017860	6	13-Dec-2023	





California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method:CPSC-CH-C1001-09.4Analytical Method:Gas Chromatography with Mass Spectrometry

Specimen N	0.	12+13	14+15			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND			1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND			1000
Conclusior	1	PASS	PASS			

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.





Client's Requirement, Phthalates content

Test Method:CPSC-CH-C1001-09.4Analytical Method:Gas Chromatography with Mass Spectrometry

Specimen N	0.	1+2+3	6	8+16	9+10+11	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	174	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	ND	ND	ND	1000
Diethyl phthalate (DEP)	84-66-2	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND	ND	ND	ND	1000
Conclusion]	PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Spacimon No	Transferre	Data of Issue	
Specimen No.	Report No.	Specimen No.	Date of Issue
1+2+3	23W-017860	1+2+3	13-Dec-2023
6	23W-017860	6	13-Dec-2023





Client's Requirement, Phthalates content

Test Method:CPSC-CH-C1001-09.4Analytical Method:Gas Chromatography with Mass Spectrometry

Specimen N	0.	12+13	14+15			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND			1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND			1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	ND			1000
Diethyl phthalate (DEP)	84-66-2	ND	ND			1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND			1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND			1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND	ND			1000
Conclusion		PASS	PASS			

Note:


mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.





Specimen description

Specimen #	Specimen description	Location
1	Silvery plated grey plastic	Tail (black style)
2	Silvery plated grey plastic	Tip (black style)
3	White plastic	Cartridge (black style)
4	Silvery metal	Spring (black style)
5	Silvery metal	Nib (black style)
6	Blue ink	Cartridge ink (black style)
7	Silvery metal	Clip (black style)
8	Silvery plated grey plastic	Middle ring (black style)
9	Offwhite coating	Barrel (offwhite style)
10	Silvery coating	Barrel (silvery style)
11	Black coating	Barrel (black style)
12	Blue coating	Barrel (blue style)
13	Red coating	Barrel (red style)
14	Orange coating	Barrel (orange style)
15	Lime coating	Barrel (lime style)
16	Black plastic	Barrel (lime style)





Sample photo:



End of the report

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and the method /regulation section(s) tested as described herein. If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule. (<u>https://www.qima.com/conditions-of-service#decisionRule</u>). This test report may not be reproduced in whole or in part, without the written approval of QIMA (Hangzhou) Testing Co., Ltd.

