

Test Report

No.: 68.431.23.2777.02R1

Date: 2023-08-03



Greater China

Applicant: Spector & Co
Address: /
Sample Description: Matte metallic finish barrel, push-action plastic ballpoint pen.
Product Type / End use: Writing instrument
Style No.: JAMES
Item No.: G1298
Supplier: USX006
Country of Origin: China
Country of Destination: CANADA & U.S.A.
Receipt Date of Sample: 2023-07-03, 2023-07-17, 2023-07-26
Date of Testing: From 2023-07-03 to 2023-08-01
Sample Submitted: The sample(s) was (were) submitted by applicant and identified.
Test Result: Refer to the data listed in following pages

Test Item	Conclusion
1. US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials	Pass*
2. US California Proposition 65 - Total Cadmium Content Test - Substrate Materials	Pass*
3. US California Proposition 65 - Total lead Content Test - Paint and Similar Surface-Coating Materials	Pass*
4. US California Proposition 65 - Total Lead Content Test - Substrate Materials	Pass*
5. Phthalates Content (11P)	Pass*
6. Tungsten Content Test	Report As Is
7. Canada Consumer Product Safety Act (S.C. 2010, c. 21), Surface Coating Materials Regulations SOR/2016-193 and SOR/2022-122 - Total Mercury	Pass
8. Canada Consumer Product Safety Act (S.C. 2010, c. 21), Surface Coating Materials Regulations SOR/2016-193 and SOR/2022-122 - Total Lead	Pass
9. Canadian Consumer Products Containing Lead Regulations SOR/2018-83 - Total Lead Content Test	Pass
10. Total Nickel Content Test	Report As Is
11. U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P)	Pass
12. US California Proposition 65 - Phthalates Content (6P)	Pass*

Remarks: 1. MDL = Method Detection Limit
2. N.D. = Not Detected (<MDL)
3. ≤ Less than
4. 1 mg/kg = 1 ppm = 0.0001%
5. NA=Not Applicable

Regd. Office: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: info@tuv sud.com
Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test: Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.23.2777.02R1

Date: 2023-08-03



Greater China

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Testing Center

Prepared by:

Authorized by:



Gianna Gao
Project Manager

Eva Liang
Project Manager

Note:

- (1) The TÜV SÜD Certification and Testing (China) Co., Ltd. "General Terms & Conditions" applied.
Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.
For further details, please see "Testing and certification regulation", chapter A-3.4
For full version, please visit: EN : <https://www.tuvsud.cn/zh-cn/resource/terms-and-conditions---en> ; SCN: <https://www.tuvsud.cn/zh-cn/terms-and-conditions> ; TCN: <https://www.tuvsud.com/zh-tw/terms-and-conditions>
- (2) The results relate only to the Items tested.
- (3) The test report shall not be reproduced except in full without the written approval of the laboratory
- (4) If relevant standards do not specify decision rule(s), follow decision rule as below:
- "Pass" means that the measured result is within the limits, even when extended by expanded uncertainty at a level of confidence of 95%.
- "Fail" means that the measured result is beyond the limit, even when extended by expanded uncertainty at a level of confidence of 95%.
- (5) The test item and sample were specified by the client.
- (6) ""*"" denotes the conclusion was drawn according to the client's specification.
- (7) This report superseded previous report 68.431.23.2777.02 issued on 2023-08-01. As per client's request, revised client's information on page 1.

Regd. Office:

Tüv Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: info@tuvsud.com
Web : <http://www.tuvsud.cn>




Lab 1 - Chemical testing and part of
electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Description of Tested Subject:

Sample	Description	Photo
A	Whole product	
001	Dark silver plated plastic (Head/ clip & end)	
002	Grey coating (On body)	

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.23.2777.02R1

Date: 2023-08-03



Greater China

Sample	Description	Photo
004	Rose golden plated plastic (Head/ clip & end)	
005	Rose golden coating (On body)	
006	Dark blue plated plastic (Head/ clip & end)	
007	Blue coating (On body)	
008	Silver plated plastic (Head/ clip & end)	
009	Silver coating (On body)	

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com





Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Sample	Description	Photo
010	Black plated plastic (Head/ clip & end)	
011	Black coating (On body)	
012	White plastic (Pen body)	
013	Grey plastic (Core)	
014	Blue ink (In core)	
015	Silver color metal (Nib of core)	
016	Silver color metal (Ball on nib of core)	
017	Silver color metal (Spring)	
018	Silvery metal (Ring)	

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.23.2777.02R1

Date: 2023-08-03



Greater China

T. No	Sample	Description
T1	001	Dark silver plated plastic (Head/ clip & end)
T2	002	Grey coating (On body)
T3	004	Rose golden plated plastic (Head/ clip & end)
T4	005	Rose golden coating (On body)
T5	006	Dark blue plated plastic (Head/ clip & end)
T6	007	Blue coating (On body)
T7	008	Silver plated plastic (Head/ clip & end)
T8	009	Silver coating (On body)
T9	010	Black plated plastic (Head/ clip & end)
T10	011	Black coating (On body)
T11	012	White plastic (Pen body)
T12	013	Grey plastic (Core)
T13	014	Blue ink (In core)
T14	015	Silver color metal (Nib of core)
T15	016	Silver color metal (Ball on nib of core)
T16	017	Silver color metal (Spring)
T17	018	Silvery metal (Ring)



Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: info@tuvsud.com
Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



Test Result(s):

1. US California Proposition 65 - Total Cadmium Content Test - Paint and Similar Surface-Coating Materials

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
002+005+007	mg/kg	10	75	N.D.	Pass
009+011	mg/kg	10	75	N.D.	Pass
014	mg/kg	10	75	N.D.	Pass

2. US California Proposition 65 - Total Cadmium Content Test - Substrate Materials

Test with reference to acid digestion or microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
001+004+006	mg/kg	10	75	N.D.	Pass
008+010	mg/kg	10	75	N.D.	Pass
012+013	mg/kg	10	75	N.D.	Pass
015	mg/kg	10	75	N.D.	Pass
016	mg/kg	10	75	N.D.	Pass
017	mg/kg	10	75	N.D.	Pass
018	mg/kg	10	75	N.D.	Pass

Remark:

- The test results of the sample 018 is transferred from sample 026 of report 68.431.23.2782.

3. US California Proposition 65 - Total Lead Content Test - Paint and Similar Surface-Coating Materials

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
002+005+007	mg/kg	10	90	N.D.	Pass
009+011	mg/kg	10	90	N.D.	Pass
014	mg/kg	10	90	N.D.	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

4. US California Proposition 65 - Total Lead Content Test - Substrate Materials

Test with reference to acid digestion or microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
001+004+006	mg/kg	10	100	N.D.	Pass
008+010	mg/kg	10	100	N.D.	Pass
012+013	mg/kg	10	100	N.D.	Pass
015	mg/kg	10	100	33.1	Pass
016	mg/kg	10	100	N.D.	Pass
017	mg/kg	10	100	N.D.	Pass
018	mg/kg	10	100	42.9	Pass

Remark:

- The test results of the sample 018 is transferred from sample 026 of report 68.431.23.2782.

5. Phthalates Content (11P)

Test with reference to in-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS).

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					001+004+006	002+005+007
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.23.2777.02R1

Date: 2023-08-03



Greater China

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					008+010	009+011
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					012+013	014
Diethyl phthalate(DEP)	84-66-2	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-n-octyl phthalate, (DNOP)	117-84-0	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



6. Tungsten Content Test

Test with reference to acid digestion and determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES)

Test items	Unit	MDL	Maximum Permissible Limit	Result(s)
				017
Tungsten(W)	mg/kg	10.0	-	N.D.
Conclusion				Report As Is

7. Canada Consumer Product Safety Act (S.C. 2010, c. 21), Surface Coating Materials Regulations SOR/2016-193 and SOR/2022-122 - Total Mercury

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
002	mg/kg	10	10.0	N.D.	Pass
005	mg/kg	10	10.0	N.D.	Pass
007	mg/kg	10	10.0	N.D.	Pass
009	mg/kg	10	10.0	N.D.	Pass
011	mg/kg	10	10.0	N.D.	Pass

8. Canada Consumer Product Safety Act (S.C. 2010, c. 21), Surface Coating Materials Regulations SOR/2016-193 and SOR/2022-122 - Total Lead

Test with reference to microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
002+005+007	mg/kg	10	90	N.D.	Pass
009+011	mg/kg	10	90	N.D.	Pass
014	mg/kg	10	90	N.D.	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuvsud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

9. Canadian Consumer Products Containing Lead Regulations SOR/2018-83 - Total Lead Content Test

Test with reference to acid digestion or microwave digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Limit	Result(s)	Conclusion
001+004+006	mg/kg	10	90	N.D.	Pass
002+005+007	mg/kg	10	90	N.D.	Pass
008+010	mg/kg	10	90	N.D.	Pass
009+011	mg/kg	10	90	N.D.	Pass
012+013	mg/kg	10	90	N.D.	Pass
014	mg/kg	10	90	N.D.	Pass
015	mg/kg	10	90	33.1	Pass
016	mg/kg	10	90	N.D.	Pass
017	mg/kg	10	90	N.D.	Pass
018	mg/kg	10	90	42.9	Pass

Remark:

- The test results of the sample 018 is transferred from sample 026 of report 68.431.23.2782.

10. Total Nickel Content Test

Test with reference to acid digestion, determination by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Sample	Unit	MDL	Client's Limit	Result(s)	Conclusion
015	mg/kg	5	-	14.059	Report As Is
016	mg/kg	5	-	1295.327	Report As Is
017	mg/kg	5	-	142.594	Report As Is
018	mg/kg	5	-	16522.062	Report As Is

Remark:

- The test results of the sample 018 is transferred from sample 026 of report 68.431.23.2782.

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of
electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

11. U.S. CFR Title 16 Part 1307 - Toys and Childcare Articles - Phthalates Content (8P)

Test with reference to in-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS).

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					001+004+006	002+005+007
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					008+010	009+011
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Parameter	CAS No.	Unit	MDL	Limit	Result(s)	
					012+013	014
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Diisobutylphthalate, (DIBP)	84-69-5	%	0.005	0.1	N.D.	N.D.
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Di-n-pentyl phthalates (DnPP)	131-18-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

12. US California Proposition 65 - Phthalates Content (6P)

Test with reference to in-house method, solvent extracted and analyzed by Gas Chromatography and Mass Spectrometry (GC-MS).

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					001+004+006	002+005+007
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					008+010	009+011
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report

No.: 68.431.23.2777.02R1

Date: 2023-08-03



Greater China

Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

Parameter	CAS No.	Unit	MDL	Client's Limit	Result(s)	
					012+013	014
Dibutyl phthalate, (DBP)	84-74-2	%	0.005	0.1	N.D.	N.D.
Bis (2-ethylhexyl) phthalate, (DEHP)	117-81-7	%	0.005	0.1	N.D.	N.D.
Benzyl butyl phthalate, (BBP)	85-68-7	%	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate, (DIDP)	26761-40-0 , 68515-49-1	%	0.005	0.1	N.D.	N.D.
Di-n-hexyl phthalate (DNHP)	84-75-3	%	0.005	0.1	N.D.	N.D.
Di-isononyl phthalate, (DINP)	28553-12-0 , 68515-48-0	%	0.005	0.1	N.D.	N.D.
Conclusion					Pass	Pass

-End of Test Report-

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuvsud.com

Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & Mechanical Test:

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China