9AI			
TEST REPORT			
Test Report #	19W-006793	Date of Report Issue:	May 20, 2019
Date of Sample Received:	May 15, 2019	Pages:	Page 1 of 18
CLIENT INFORMATION:			1. K. H. A
Company:	Spector & Co.		
Address:	-		
SAMPLE INFORMATION:			
Description:	BALLPOINT PEN		0/0 <mark>3/00/23430/03/01223</mark> 436/8312
Assortment:	ххх		
Model/style No.:	ADMIRAL		
SKU No.:	G4019		
Factory/Supplier:	USN014		
Quantity Submitted:	3 pcs per color		
Country of Distribution:	Canada, United States		
Country of Origin:	China		
Testing Period:	05/15/2019-05/20/2019		

OVERALL RESULT:

PASS with information

Refer to page 2 for test result summary and appropriate notes.

HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD

Kein.be

Kevin Lee Technical Manager



ECTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



19W-006793 May 15, 2019 Date of Report Issue:May 20, 2019Pages:Page 2 of 18

TEST RESULTS SUMMARY:

Date of Sample Received:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	California Proposition 65, Total Lead in Paints and Surface Coatings
PASS	California Proposition 65, Total Lead in Substrate Materials
PASS	Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead in Paints and Surface Coatings
PASS	Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content
PASS	California Proposition 65, Total Cadmium in Paints and Surface Coatings
PASS	California Proposition 65, Total Cadmium in Substrate Materials
Refer to Detailed Results	Client's Requirement, Total Tungsten content
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)
PASS	CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates(DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)
PASS	Client's Requirement, Phthalates content



ECTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



DETAILED RESULTS:

California Proposition 65, Total Lead in Paints and Surface Coatings

Test Method:CPSC-CH-E1003-09.1Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3+4	6			Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND			90
Conclusion	PASS	PASS	PASS			

Note: mg/kg =Milligrams per kilogram LT = Less than ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



CTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



Pages:

DETAILED RESULTS:

California Proposition 65, Total Lead in Substrate Materials

Test Method:CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5	7+8+11	9	10+16	12	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	13+14	15				Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	42				100
Conclusion	PASS	PASS				

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit =15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



CTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



Pages:

DETAILED RESULTS:

Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead in Paints and Surface Coatings

Test Method:ASTM F963-17 Clause 8.3.1Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3+4	6			Total
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Limit (mg/kg)
Total Lead (Pb)	ND	ND	ND			90
Conclusion	PASS	PASS	PASS			

Note:

mg/kg=Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit: Pb=15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.



CTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



Pages:

DETAILED RESULTS:

Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content

Test Method:	ASTM F963-17 Clause 8.3.1
Analytical Method:	Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5	7+8+11	9	10+16	12	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	13+14	15				Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	42				90
Conclusion	PASS	PASS				

Note:

mg/kg=Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.



CTION TESTING TECHNOLOGY CO., LTD
Email: LabTesting@qima.com
Tel: (86) 571 8999 7158
A2 Building
No. 1213 Huoju South Road
Puyan Street
Binjiang District
Hangzhou
China



Pages:

DETAILED RESULTS:

California Proposition 65, Total Cadmium in Paints and Surface Coatings

Test Method:ASTM F963-17 Clause 8.3.1Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3+4	6			Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND	ND	ND			75
Conclusion	PASS	PASS	PASS			

Note: mg/kg =Milligrams per kilogram LT = Less than ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



CTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



Pages:

DETAILED RESULTS:

California Proposition 65, Total Cadmium in Substrate Materials

Test Method:ASTM F963-17 Clause 8.3.1Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5	7+8+11	9	10+16	12	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND	ND	ND	ND	ND	75
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	13+14	15				Limit
Tost Itom	Result	Result	Result	Result	Result	(mg/kg)
Test Item	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(8/8/
Total Cadmium (Cd)	ND	ND				75
Conclusion	PASS	PASS				

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



CTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



Pages:

DETAILED RESULTS:

Client's Requirement, Total Tungsten content

Test Method:US EPA 3052:1996 & US EPA 6010D:2014Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5+9	12+15				Limit
Testites	Result	Result	Result	Result	Result	(mg/kg)
Test Item	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(8/8/
Total Tungsten (W)	36	1970				
Conclusion	Information	Information				
Conclusion	only	only				

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.



CTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



Pages:

DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method:	CPSC-CH-C1001-09.4
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen N	0.	1+2	3+4	6	7+8+11	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion	ı	PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



CTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



Pages:

DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method:	CPSC-CH-C1001-09.4
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen N	0.	10+16	13+14			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND			1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND			1000
Conclusion	ı	PASS	PASS			

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.



CTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



Pages:

DETAILED RESULTS:

CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method:	CPSC-CH-C1001-09.4(Modified), In-House Method
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen N	0.	1+2	3+4	6	7+8+11	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusior	1	PASS	PASS	PASS	PASS	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.



CTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



Pages:

DETAILED RESULTS:

CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method:	CPSC-CH-C1001-09.4(Modified), In-House Method
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen N	0.	10+16	13+14			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND			1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND			1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND			1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND			1000
Conclusior	ı	PASS	PASS			

Note:

mg/kg = Milligrams per kilogram LT = Less than

LI = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.



CTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



DETAILED RESULTS:

Client's Requirement, Phthalates content

Test Method:	CPSC-CH-C1001-09.4
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen No).	1+2	3+4	6	7+8+11	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	ND	ND	ND	1000
Diethyl phthalate (DEP)	84-66-2	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



DETAILED RESULTS:

Client's Requirement, Phthalates content

Test Method:	CPSC-CH-C1001-09.4
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen No.		10+16	13+14			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND			1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND			1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	ND			1000
Diethyl phthalate (DEP)	84-66-2	ND	ND			1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND			1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND			1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND	ND			1000
Conclusion		PASS	PASS			

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



Pages:

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location	
1	Silvery coating	Barrel	
2	Red coating	Barrel	
3	Blue coating	Barrel	
4	Black coating	Barrel	
5	Silvery metal	Barrel	
6	Black ink	Cartridge(grey style)	
7	Grey plastic	Cartridge(grey style)	
8	Black plastic	Gear(grey style)	
9	Silvery metal	Spring(grey style)	
10	Black soft plastic	Slide paw(grey style)	
11	Black plastic	Grip(grey style)	
12	Silvery metal	Clip(grey style)	
13	Silvery plated light grey plastic	Tip(grey style)	
14	Silvery plated light grey plastic	Button(grey style)	
15	Silvery metal	Nib(grey style)	
16	Black plastic	Top of barrel(grey style)	



BECTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China



Pages:

SAMPLE PHOTO:







This test report may not be reproduced in whole or in part, without written approval of Hangzhou Asiainspection Testing Technology Co., Ltd



Pages:

SAMPLE PHOTO:



-End Report-



ECTION TESTING TECHNOLOGY CO., LTD • Email: LabTesting@qima.com • Tel: (86) 571 8999 7158 A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • China