

## **TEST REPORT**

Test Report # 23W-002556 Date of Report Issue: March 10, 2023

Date of Sample Received: March 6, 2023 Pages: Page 1 of 24

**CLIENT INFORMATION:** 

Company: Spector & Co.

Address: testing@spectorandco.com

**SAMPLE INFORMATION:** 

Description: Solid white plastic 3in1 stylus/highlighter/ballpoint pen

Assortment: BLK/BLU/GRN/ORG/PPL/RED/WHT

PO No.:

Item No./Name: I149

Item Class:

Factory/Supplier: USS049
Country of Origin: China

Country of Distribution: Canada, United States
Testing Period: 03/07/2023-03/10/2023

**OVERALL RESULT:** 

**PASS** with information

Please refer to the following pages for test result summary and appropriate notes.

QIMA (HANGZHOU) TESTING CO., LTD.

Loremy. Xu

Jeremy Xu

RC-CSHZ-R063

Chemical Laboratory Supervisor

OIMA Nangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1,No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China
Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with ' $\phi$ ' was subcontracted to external laboratory.



Test Report #: 23W-002556 Page 2 of 24

## **TEST RESULTS SUMMARY:**

RC-CSHZ-R063

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	California Proposition 65, Total Lead in Paints and Surface Coatings
PASS	California Proposition 65, Total Lead in Substrate Materials
PASS	Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead and Mercury in Stickers, Films and Surface Coating Materials
PASS	Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content
PASS	California Proposition 65, Total Cadmium in Paints and Surface Coatings
PASS	California Proposition 65, Total Cadmium in Substrate Materials
Information only	Client's requirement, Total Nickel content
Information only	Client's Requirement, Total Tungsten content
PASS	CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)
PASS	Client's Requirement, Phthalates content



Test Report #: 23W-002556 Page 3 of 24

#### **DETAILED RESULTS:**

#### California Proposition 65, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	7	12+26				Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND				90
Conclusion	PASS	PASS				

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

#### Remark:

RC-CSHZ-R063

The specification is quoted from client's requirement.

Ī	Specimen No	Transferre	Transferred from				
	Specimen No.	Report No.	Specimen No.	Date of Issue			
	7	23W-002559	7	March 10, 2023			



Test Report #: 23W-002556 Page 4 of 24

#### **DETAILED RESULTS:**

## California Proposition 65, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+16+17	2+4+6	3+20+21	5	8	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	9	10	11	13+19+22	14+15+18	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	38	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	23+24+25					Limit
Test Item	Result	Result	Result	Result	Result	(mg/kg)
	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(1118/18)
Total Lead (Pb)	ND					100
Conclusion	PASS					

#### Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit =15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

#### Remark:

RC-CSHZ-R063

The specification is quoted from client's requirement.



Page 5 of 24 Test Report #: 23W-002556

## Data Consolidation Reference:

检验检测专用章

RC-CSHZ-R063

Cnasiman Na	Transferre	Date of Issue	
Specimen No.	Report No.	Specimen No.	Date of issue
1+16+17	23W-002559	1+12+13	March 10, 2023
2+4+6	23W-002559	2+3+5	March 10, 2023
5	23W-002559	4	March 10, 2023
8	23W-002559	8	March 10, 2023
9	23W-002559	9	March 10, 2023
14+15+18	23W-002559	10+11+14	March 10, 2023



Test Report #: 23W-002556 Page 6 of 24

#### **DETAILED RESULTS:**

# Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead and Mercury in Stickers, Films and Surface Coating Materials

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	7	12+26				Total
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Limit (mg/kg)
Total Lead (Pb)	ND	ND				90
Total Mercury (Hg)	ND	ND				10
Conclusion	PASS	PASS				

Note:

mg/kg=Milligrams per kilogram

LT = Less than

RC-CSHZ-R063

ND = Not detected (Reporting Limit: Pb=15 mg/kg; Hg = 10 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Specimen No	Transferre	ed from	Date of Issue
Specimen No.	Report No.	eport No. Specimen No.	
7	23W-002559	7	March 10, 2023



Test Report #: 23W-002556 Page 7 of 24

#### **DETAILED RESULTS:**

## Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+16+17	2+4+6	3+20+21	5	7	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	8	9	10	11	12+26	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	39	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	13+19+22	14+15+18	23+24+25			Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND ND	ND			90
Conclusion	PASS	PASS	PASS			

#### Note:

mg/kg=Milligrams per kilogram)

LT = Less than

RC-CSHZ-R063

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

#### Data Consolidation Reference:

Specimen No.	Transferre	Date of Issue	
	Report No.	Report No. Specimen No.	
1+16+17	23W-002559	1+12+13	March 10, 2023
2+4+6	23W-002559	2+3+5	March 10, 2023
5	23W-002559	4	March 10, 2023
7	23W-002559	7	March 10, 2023
8	23W-002559	8	March 10, 2023
9	23W-002559	9	March 10, 2023
14+15+18	23W-002559	10+11+14	March 10, 2023

OIMA Nangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1,No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China
Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with ' $\phi$ ' was subcontracted to external laboratory.



Test Report #: 23W-002556 Page 8 of 24

#### **DETAILED RESULTS:**

## California Proposition 65, Total Cadmium in Paints and Surface Coatings

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	7	12+26				Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND	ND				75
Conclusion	PASS	PASS				

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

#### Remark:

RC-CSHZ-R063

The specification is quoted from client's requirement.

Specimen No	Transferre	ed from	Data of Issue
Specimen No.	Report No.	Specimen No.	Date of Issue
7	23W-002559	7	March 10, 2023



Test Report #: 23W-002556 Page 9 of 24

#### **DETAILED RESULTS:**

## California Proposition 65, Total Cadmium in Substrate Materials

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+16+17	2+4+6	3+20+21	5	8	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND	ND	ND	ND	ND	75
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	9	10	11	13+19+22	14+15+18	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND	ND	ND	ND	ND	75
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	23+24+25					Limit
Test Item	Result	Result	Result	Result	Result	(mg/kg)
rest item	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(8/8/
Total Cadmium (Cd)	ND					75
Conclusion	PASS					

#### Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

#### Remark:

RC-CSHZ-R063

The specification is quoted from client's requirement.



Page 10 of 24 Test Report #: 23W-002556

## Data Consolidation Reference:

检验检测专用章

RC-CSHZ-R063

Specimen No.	Transferre	Data of Issue		
Specimen No.	Report No. Specimen No.		— Date of Issue	
1+16+17	23W-002559	1+12+13	March 10, 2023	
2+4+6	23W-002559	2+3+5	March 10, 2023	
5	23W-002559	4	March 10, 2023	
8	23W-002559	8	March 10, 2023	
9	23W-002559	9	March 10, 2023	
14+15+18	23W-002559	10+11+14	March 10, 2023	



Test Report #: 23W-002556 Page 11 of 24

#### **DETAILED RESULTS:**

## Client's requirement, Total Nickel content

Test Method: US EPA 3052:1996 & US EPA 6010D:2014

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5+8+9					Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Nickel(Ni)	65052					
Conclusion	Information only					

Note:

RC-CSHZ-R063

mg/kg = Milligrams per kilogram

ND = Not detected (report limit = 30 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Cnasiman Na	Transferre	ed from	Date of Issue
Specimen No.	Report No.	Specimen No.	Date of issue
5+8+9	23W-002559	4+8+9	March 10, 2023



Test Report #: 23W-002556 Page 12 of 24

#### **DETAILED RESULTS:**

## Client's Requirement, Total Tungsten content

Test Method: US EPA 3052:1996 & US EPA 6010D:2014

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5+8+9					Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Tungsten (W)	512					
Conclusion	Information only					

Note:

RC-CSHZ-R063

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Cnasiman Na	Transferre	Transferred from				
Specimen No.	Report No. Specimen No.		Date of Issue			
5+8+9	23W-002559	4+8+9	March 10, 2023			



Test Report #: 23W-002556 Page 13 of 24

#### **DETAILED RESULTS:**

CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1+16+17	2+4+6	3+20+21	7	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusion	1	PASS	PASS	PASS	PASS	

### Note:

RC-CSHZ-R063

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

## Data Consolidation Reference:

	Cnooiman No	Transferre	Data of Issue	
	Specimen No.	Report No.	Specimen No.	Date of Issue
	1+16+17	23W-002559	1+12+13	March 10, 2023
	2+4+6	23W-002559	2+3+5	March 10, 2023
	7	23W-002559	7	March 10, 2023

OIMA Nangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1,No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China
Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with  $'\phi'$  was subcontracted to external laboratory.

神e te result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein. 機能機制用章 fit is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule (https://www.aima.com/conditions-of-service#decisionRule).



Test Report #: 23W-002556 Page 14 of 24

#### **DETAILED RESULTS:**

CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		10	12+26	13+19+22	14+15+18	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusion	1	PASS	PASS	PASS	PASS	

#### Note:

mg/kg = Milligrams per kilogram

LT = Less than

RC-CSHZ-R063

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

## Data Consolidation Reference:

Specimen No.	Transferre	ed from	Data of Issue
Specimen No.	Report No.	Specimen No.	Date of Issue
14+15+18	23W-002559	10+11+14	March 10, 2023

OIMA Nangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1,No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China
Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with  $'\phi'$  was subcontracted to external laboratory.



Test Report #: 23W-002556 Page 15 of 24

#### **DETAILED RESULTS:**

CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		23+24+25				Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND				1000
Benzyl butyl phthalate (BBP)	85-68-7	ND				1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND				1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND				1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND				1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND				1000
Diisobutyl phthalate (DIBP)	84-69-5	ND				1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND				1000
Conclusion	1	PASS				

#### Note:

RC-CSHZ-R063

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.



Test Report #: 23W-002556 Page 16 of 24

#### **DETAILED RESULTS:**

## California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1+16+17	2+4+6	3+20+21	7	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion	1	PASS	PASS	PASS	PASS	

## Note:

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

#### Remark:

RC-CSHZ-R063

The specification is quoted from client's requirement.

#### Data Consolidation Reference:

Cassimon No	Transferre	Date of Issue	
Specimen No.	Report No.	Specimen No.	Date of issue
1+16+17	23W-002559	1+12+13	March 10, 2023
2+4+6	23W-002559	2+3+5	March 10, 2023
7 23W-002559		7	March 10, 2023

OIMA Nangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1,No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China
Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with  $'\phi'$  was subcontracted to external laboratory.

神e te result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein. 機能機制用章 fit is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule (https://www.aima.com/conditions-of-service#decisionRule).



Test Report #: 23W-002556 Page 17 of 24

#### **DETAILED RESULTS:**

## California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		10	12+26	13+19+22	14+15+18	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion	1	PASS	PASS	PASS	PASS	

#### Note:

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

#### Remark:

RC-CSHZ-R063

The specification is quoted from client's requirement.

	Specimen No	Transferre	ed from	Data of Issue
	Specimen No.	Report No.	Specimen No.	Date of Issue
	14+15+18	23W-002559	10+11+14	March 10, 2023



Test Report #: 23W-002556 Page 18 of 24

#### **DETAILED RESULTS:**

## California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		23+24+25				Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND				1000
Benzyl butyl phthalate (BBP)	85-68-7	ND				1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND				1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND				1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND				1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND				1000
Conclusion	1	PASS				

#### Note:

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

#### Remark:

RC-CSHZ-R063

The specification is quoted from client's requirement.



Test Report #: 23W-002556 Page 19 of 24

## **DETAILED RESULTS:**

RC-CSHZ-R063

## Client's Requirement, Phthalates content

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1+16+17	2+4+6	3+20+21	7	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	ND	ND	ND	1000
Diethyl phthalate (DEP)	84-66-2	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	



Test Report #: 23W-002556 Page 20 of 24

Note:

RC-CSHZ-R063

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

	Chasiman Na	Transferre	Date of Issue	
	Specimen No.	Report No.	Specimen No.	Date of issue
Ī	1+16+17	23W-002559	1+12+13	March 10, 2023
Ī	2+4+6	23W-002559	2+3+5	March 10, 2023
Ī	7	23W-002559	7	March 10, 2023



Test Report #: 23W-002556 Page 21 of 24

#### **DETAILED RESULTS:**

## Client's Requirement, Phthalates content

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		10	12+26	13+19+22	14+15+18	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	ND	ND	ND	1000
Diethyl phthalate (DEP)	84-66-2	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

#### Note:

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

RC-CSHZ-R063

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

#### Data Consolidation Reference:

Specimen No.	Transferre	Data of Issue	
	Report No.	Specimen No.	Date of Issue
14+15+18	23W-002559	10+11+14	March 10, 2023

OIMA Nangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1,No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China
Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with ' $\phi$ ' was subcontracted to external laboratory.



Test Report #: 23W-002556 Page 22 of 24

#### **DETAILED RESULTS:**

## Client's Requirement, Phthalates content

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No	).	23+24+25				Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND				1000
Benzyl butyl phthalate (BBP)	85-68-7	ND				1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND				1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND				1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND				1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND				1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND				1000
Diethyl phthalate (DEP)	84-66-2	ND				1000
Diisobutyl phthalate (DIBP)	84-69-5	ND				1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND				1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND				1000
Conclusion		PASS				

#### Note.

mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)


LT = Less than

RC-CSHZ-R063

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Test(s) marked with ' $\phi$ ' was subcontracted to external laboratory.





Test Report #: 23W-002556

## **SPECIMEN DESCRIPTION:**

检验检测专用章

RC-CSHZ-R063

Specimen No.	Specimen Description	Location
1	Red plastic	Grip (red style)
2	White plastic	Barrel (red style)
3	Red plastic	Barrel upper (red style)
4	Silvery plated grey plastic	Button (red style)
5	Silvery metal	Clip (red style)
6	Grey plastic	Cartridge (red style)
7	Blue ink	Cartridge (all styles)
8	Silvery metal	Spring (red style)
9	Silvery metal	Nib (red style)
10	Black soft plastic	Tip (red style)
11	Yellow fiber	Fluorescent pen (all styles)
12	Yellow ink	Fluorescent pen (all styles)
13	Translucent plastic	Cap of fluorescent pen (red style)
14	Black plastic	Grip (black style)
15	Blue plastic	Grip (blue style)
16	Green plastic	Grip (green style)
17	Purple plastic	Grip (purple style)
18	Orange plastic	Grip (orange style)
19	Translucent plastic	Grip (white style)
20	Black plastic	Barrel upper (black style)
21	Blue plastic	Barrel upper (blue style)
22	Green plastic	Barrel upper (green style)
23	Purple plastic	Barrel upper (purple style)
24	Orange plastic	Barrel upper (orange style)
25	White plastic	Barrel upper (white style)
26	White coating	Barrel (all styles)

QIMA Nangzhou) Testing Co., Ltd. • Room 401,4-5/F, Building 1,No.1213 Huoju South Road, Puyan Subdistrict, Binjiang District, Hangzhou, China Email: Labtesting@qima.com • Tel: (86) 571 8999 7158.

Test(s) marked with ' $\phi$ ' was subcontracted to external laboratory.

The terresult(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein. f it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule (https://www.gima.com/conditions-of-service#decisionRule).





Test Report #: 23W-002556

## **SAMPLE PHOTO:**

RC-CSHZ-R063





-End Report-

Test(s) marked with ' $\phi^{\prime}$  was subcontracted to external laboratory.