




TEST REPORT

Test Report # 18W-000972 Date of Report Issue: March 6, 2018
Date of Sample Received: March 2, 2018 Pages: Page 1 of 9

CLIENT INFORMATION:

Company: Spector & Co.
Address: -



SAMPLE INFORMATION:

Description: Non Coated Nomad Fabric
Assortment: Grey
Model/style No.: Nomad
SKU No.: Raw material Nomad Non coated Fabric
Factory/Supplier: -
Quantity Submitted: 1
Country of Distribution: Canada & USA
Country of Origin: China
Testing Period: 03/02/2018-03/06/2018

OVERALL RESULT:

PASS

Refer to page 2 for test result summary and appropriate notes.

HANGZHOU ASIAINSPECTION
TECHNOLOGY CO., LTD

Kevin Lee
Technical Manager





TEST REPORT

Test Report # 18W-000972 Date of Report Issue: March 6, 2018
 Date of Sample Received: March 2, 2018 Pages: Page 2 of 9

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	California Proposition 65, Total Lead in Substrate Materials
PASS	California Proposition 65, Total Cadmium in Substrate Materials
PASS	Client's Requirement, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP, DNOP, DEP)
PASS	SOR/2016-194 and Method F01 Flammability of Textile Products
PASS	Flammability Test of Clothing Textiles





DETAILED RESULTS:

California Proposition 65, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	---	---	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	---	---	---	---	100
Conclusion	PASS	---	---	---	---	

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit =15 mg/kg)

Remark:

The specification is quoted from client’s requirement.





DETAILED RESULTS:

California Proposition 65, Total Cadmium in Substrate Materials

Test Method: ASTM F963-17 Clause 8.3.1
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	---	---	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Cadmium (Cd)	ND	---	---	---	---	75
Conclusion	PASS	---	---	---	---	

Note:
mg/kg =Milligrams per kilogram
LT = Less than
ND = Not detected (Reporting Limit = 15 mg/kg)

Remark:
The specification is quoted from client’s requirement.



**DETAILED RESULTS:****Client's Requirement, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP, DNOP, DEP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.	1	---	---	---	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	---	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	---	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	---	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	---	---	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	---	---	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	---	---	1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	---	---	1000
Diethyl phthalate (DEP)	84-66-2	ND	---	---	1000
Conclusion		PASS	---	---	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Remark:

The specification is quoted from client's requirement.



**DETAILED RESULTS:****SOR/2016-194 and Method F01 Flammability of Textile Products**

Test Method: CAN/CGSB-4.2 No.27.5-2008

Specimen No.	1				
Preliminary Tests	<u>Fabric Surface</u>	Smooth	<u>Test Specimen Direction</u>		Length
Items	Result				Client's requirement
	<u>As Received</u>		<u>After Dry-cleaning and Laundering*</u>		
	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	<u>Flame Spread (sec.)</u>	<u>Burn Code</u>	
(1)	-	IBE	-	IBE	>3.5s
(2)	-	IBE	-	IBE	
(3)	-	IBE	-	IBE	
(4)	-	IBE	-	IBE	
(5)	-	IBE	-	IBE	
(6)	-	IBE	-	IBE	
(7)	-	IBE	-	IBE	
(8)	-	IBE	-	IBE	
(9)	-	IBE	-	IBE	
(10)	-	IBE	-	IBE	
Conclusion	PASS				

* Dry-cleaning / Laundering procedure is according to CAN/CGSB-4.2 No.30.3-94 & CAN/CGSB-4.2 No.58-2004; Machine wash at 50°C and tumble dry on the normal setting.

Burn Code Description:

IBE = Ignited but extinguished



**DETAILED RESULTS:****Flammability Test of Clothing Textiles**

Test Method: 16 CFR Part 1610 - March 25, 2008 Edition

Specimen No.	1	
Items	Result	Client's requirement
Specific exemptions	After testing, fabric weight of sample is 4.84 oz / sq. yd. Thus the sample is exempt from flammability testing in accordance with 16 CFR 1610.1(d)(1): Plain surface fabric with fabric weight \geq 2.6 oz/sq. yd.	Class I
Conclusion	PASS	






SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Grey textile	Main body





SAMPLE PHOTO:



-End Report-

