PAI			
TEST REPORT			
Test Report #	18W-003309	Date of Report Issue:	June 28, 2018
Date of Sample Received:	June 5, 2018	Pages:	Page 1 of 14
CLIENT INFORMATION:			
Company:	Spector & Co.		
Address:	-		
SAMPLE INFORMATION:			
Description:	8,000 mAh POWER BANI	K	
Assortment:	BLK,BRN,WHT,NVY,GRY		
Model/style No.:	FABRIZIO		
SKU No.:	T113		
Factory/Supplier:	USU019		
Quantity Submitted:	15 PCS		
Country of Distribution:	Canada ,USA		
Country of Origin:	China		
Testing Period:	06/05/2018-06/08/2018	,06/26/2018-06/28/2018	

OVERALL RESULT:

PASS

Refer to page 2 for test result summary and appropriate notes.

HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD

Keim.lee

Kevin Lee Technical Manager





Test Report #18W-003309Date of Sample Received:June 5, 2018

Date of Report Issue:June 28, 2018Pages:Page 2 of 14

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	California Proposition 65, Total Lead in Substrate Materials
PASS	Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates
PASS	California Proposition 65, Total Cadmium in Substrate Materials
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)
PASS	CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates(DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)
PASS	Client's Requirement, Phthalates content



HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD

• Email: Labtesting@asiainspection.com • Tel: (8

• 5/F A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • C



Pages:

DETAILED RESULTS:

California Proposition 65, Total Lead in Substrate Materials

Test Method:CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3+4	5	6+7+9	8	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	23	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	10	11+13+14	12	15		Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	ND		100
Conclusion	PASS	PASS	PASS	PASS		

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit =15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Data Consolidation Reference:

Specimen No	Transferre	Date of Issue	
Specimen No.	Report No.	Specimen No.	Date of issue
5	18W-000907-S1	1	June 7, 2018





Pages:

DETAILED RESULTS:

Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates

Test Method:CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3+4	5	6+7+9	8	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	23	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	10	11+13+14	12	15		Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Lead (Pb)	ND	ND	ND	ND		90
Conclusion	PASS	PASS	PASS	PASS		

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Data Consolidation Reference:

Specimen No.	Transferre	Date of Issue	
Specimen No.	Report No.	Specimen No.	Date of issue
5	18W-000907-S1	1	June 7, 2018



HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD • Email: Labtesting@asiainspection.com • Tel: (8 • 5/F A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • CN



Pages:

DETAILED RESULTS:

California Proposition 65, Total Cadmium in Substrate Materials

Test Method:ASTM F963-17 Clause 8.3.1Analytical Method:Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3+4	5	6+7+9	8	Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND	ND	ND	ND	ND	75
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	10	11+13+14	12	15		Limit
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Total Cadmium (Cd)	ND	ND	ND	ND		75
Conclusion	PASS	PASS	PASS	PASS		

Note:

mg/kg =Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

Data Consolidation Reference:

Specimen No.	Transferre	Date of Issue	
Specifien No.	Report No.	Specimen No.	Date of issue
5	18W-000907-S1	1	June 7, 2018





Pages:

DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method:	CPSC-CH-C1001-09.3
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen N	0.	1+2+3	4+5	6+7+9	10	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion	ı	PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.





Pages:

DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method:	CPSC-CH-C1001-09.3
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen N	0.	11+13+14	16			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	612			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND			1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND			1000
Conclusior	1 <u> </u>	PASS	PASS			

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.





Pages:

DETAILED RESULTS:

CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method:	CPSC-CH-C1001-09.3(Modified), In-House Method
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen N	0.	1+2+3	4+5	6+7+9	10	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusior	1	PASS	PASS	PASS	PASS	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.





Pages:

DETAILED RESULTS:

CPSC 16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)

Test Method:	CPSC-CH-C1001-09.3(Modified), In-House Method
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen N	0.	11+13+14	16			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	612			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND			1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND			1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND			1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND			1000
Conclusior	1	PASS	PASS			

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.





Pages:

DETAILED RESULTS:

Client's Requirement, Phthalates content

Test Method:	CPSC-CH-C1001-09.3
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen No).	1+2+3	4+5	6+7+9	10	Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	ND	ND	ND	1000
Diethyl phthalate (DEP)	84-66-2	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.





DETAILED RESULTS:

Client's Requirement, Phthalates content

Test Method:	CPSC-CH-C1001-09.3
Analytical Method:	Gas Chromatography with Mass Spectrometry

Specimen No).	11+13+14	16			Limit
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	(mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND			1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND			1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	612			1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND			1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND			1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND			1000
Di-n-octyl phthalate (DNOP)	117-84-0	ND	ND			1000
Diethyl phthalate (DEP)	84-66-2	ND	ND			1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND			1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND			1000
Di-n-pentyl phthalate (DPENP/DnPP)	131-18-0	ND	ND			1000
Conclusion		PASS	PASS			

Note:

mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.





Pages:

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	White synthetic leather	Power bank(white style)
2	Blue synthetic leather	Power bank(blue style)
3	Grey synthetic leather	Power bank(grey style)
4	Black synthetic leather	Power bank(black style)
5	Brown synthetic leather	Power bank(brown style)
6	Black plastic	Power bank(all styles)
7	Grey and black plastic	Faucet
8	Silver metal	Faucet
9	Black plastic	Button
10	Black soft plastic	Main body of USB cable
11	Black plastic	Connector
12	Silver metal	Connector
13	White plastic	Connector
14	Grey and black plastic	Small connector
15	Silver metal	Small connector
16	Black plastic	Adjustable buckle





Pages:

SAMPLE PHOTO:







HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD • Email: Labtesting@asiainspection.com • Tel: (86 • 5/F A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • C



Pages:

Page 14 of 14

SAMPLE PHOTO:



-End Report-



HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD • Email: Labtesting@asiainspection.com • Tel: (8 • 5/F A2 Building • No. 1213 Huoju South Road • Puyan Street • Binjiang District • Hangzhou • C